

PHOTODEGRADATION OF BIOPOLYMER DOPED WITH TITANIUM
DIOXIDE (TiO₂) AS ULTRAVIOLET (UV) STABILIZER

SITI RAHMAH BINTI MOHID

A thesis submitted in
fulfilment of the requirement for the award of the
Degree of Master of Mechanical Engineering

Faculty of Mechanical and Manufacturing Engineering
Universiti Tun Hussein Onn Malaysia

MAY 2015

ABSTRACT

A large amount of waste cooking oil has become an environmental issue around the world. This oil is renewable and biodegradable than the corresponding products made from petroleum sources. The major concern in this study focuses on the resistance of the biopolymer to ultraviolet (UV) light exposure. The virgin oil (VO) and waste oil (WO) was converted into biomonomer. By adding biomonomer with an appropriate amount of 4, 4'-methylene diphenyl diisocyanate (MDI) and solvent, the virgin oil polymer (VOP) and waste oil polymer (WOP) were produced. The biopolymer (BP) were added with low loading metal oxide filler which is 2.5, 5, 7.5 and 10 % of titanium dioxide (TiO_2) to form biopolymer composite (BPC). The resistance to UV light and mechanical properties of BP and BPC were determined after exposure the thin films in UV weatherometer for an extended period of time at 250, 500, 750, 1000, 2000 and 3000 hours. The results based on the spectroscopic analysis of UV-Vis and FTIR confirmed the photodegradation processes of BP and BPC of VOP and WOP. The increasing absorbance in UV-Vis spectra indicated the formation of quinone after UV-irradiation of BP and BPC of VOP and WOP. Furthermore, BP thin films shows rapid loss of tensile strength but the increased loading of TiO_2 can improve mechanical performance. Visual inspection based on the colour changes of the thin films showed quinone (yellow) formation of the irradiated films of BP and BPC of VOP and WOP. As a conclusion, the effect of prolonged exposure to UV light, in general promotes photo degradation for BP but BPC gives slower chemical modification. The innovative biopolymer composite were successfully designed and developed by adding the TiO_2 as UV stabilizer to reduce the photo-degradation of the biopolymer.

ABSTRAK

Sejumlah besar sisa minyak masak telah menjadi isu alam sekitar di seluruh dunia. Minyak ini merupakan produk yang boleh diperbaharui dan lebih mudah terbiodegradasi berbanding produk dari sumber petroleum. Tumpuan utama dalam kajian ini fokus kepada rintangan biopolimer terhadap pendedahan cahaya ultraungu (UV). Minyak dara (VO) dan sisa minyak (WO) telah ditukar kepada biomonomer. Dengan menambah biomonomer dengan jumlah yang sesuai 4, 4'-methylene diphenyl diisocyanate (MDI) dan pelarut, polimer minyak dara (VOP) dan polimer sisa minyak (WOP) telah dihasilkan. Biopolimer (BP) telah ditambah dengan pengisi logam oksida yang rendah iaitu 2.5, 5.0, 7.5 dan 10.0 % daripada titanium dioksida (TiO_2) untuk membentuk biopolimer komposit (BPC). Rintangan kepada cahaya UV dan sifat mekanik BP dan BPC telah ditentukan selepas pendedahan filem nipis di dalam alat weatherometer UV untuk tempoh masa yang panjang pada 250, 500, 750, 1000, 2000 dan 3000 jam. Keputusan berdasarkan analisis spektroskopi UV-Vis dan FTIR menunjukkan proses degradasi foto bagi BP dan BPC dari VOP dan WOP. Keserapan meningkat di UV-Vis spektrum menunjukkan pembentukan *quinone* selepas penyinaran-UV bagi BP dan BPC dari VOP dan WOP. Tambahan pula, BP filem nipis menunjukkan kehilangan yang cepat bagi kekuatan tegangan tetapi peningkatan TiO_2 boleh meningkatkan prestasi mekanikal. Pemeriksaan visual berdasarkan perubahan warna daripada filem nipis menunjukkan pembentukan *quinone* (kuning) oleh pancaran sinaran filem BP dan BPC dari VOP dan WOP. Kesimpulannya, kesan pendedahan yang berpanjangan kepada cahaya UV, secara amnya menggalakkan degradasi foto untuk BP tetapi BPC memberikan pengubahsuaian kimia secara perlahan. Komposit biopolimer inovatif telah berjaya direka dan dibangunkan dengan menambah TiO_2 sebagai penstabil UV untuk mengurangkan degradasi foto oleh biopolimer.

CONTENTS

TITLE	
DECLARATION	
DEDICATION	
ACKNOWLEDGEMENT	
ABSTRACT	
ABSTRAK	
CONTENTS	i
LIST OF FIGURE	vi
LIST OF TABLE	x
LIST OF SYMBOL AND ABBREVIATIONS	xii
LIST OF APPENDICES	xiv
CHAPTER 1 INTRODUCTION	1
1.1 Introduction	1
1.2 Background of study	3
1.3 Problem statement	4
1.4 Importance/significance of study	5
1.5 Objective of the study	6

1.6	Scope of the study	6
CHAPTER 2 LITERATURE REVIEW		7
2.1	Polymer	7
2.2	Materials for development of biopolymer (BP) and biopolymer composite (BPC)	12
2.2.1	Monomer based on renewable resources	12
2.2.2	Biopolymer composite (BPC) from renewable resources	15
2.2.3	Methylene diphenyl diisocyanate (MDI) and toluene diisocyanate (TDI) as aromatic isocyanates	17
2.2.4	Titanium dioxide (TiO ₂) in polymer	19
2.2.5	Titanium dioxide (TiO ₂) as photocatalyst	22
2.3	Types of polymers degradation	23
2.3.1	Photo-oxidative degradation	24
2.3.2	Thermal degradation	27
2.3.3	Ozone induced degradation	28
2.3.4	Mechanochemical degradation	29
2.3.5	Catalytic degradation	30
2.3.6	Biodegradation	32
2.4	Polymer stabilization	34
2.4.1	Hindered amine lights stabilizer (HALS)	37
2.4.2	UV absorber (UVA)	38



PTTA UTHM
PERPUSTAKAAN TUN AMINAH

2.4.3	Antioxidant	39
2.4.4	Light screener	41
2.4.5	Radical scavenger	43
2.5	Artificial weathering for polymeric materials	44
2.6	Fourier transform infrared (FTIR) for polymeric materials	49
2.6.2	FTIR for polymeric materials under UV irradiation	52
2.7	Mechanical properties of polymer materials	54
2.8	Ultraviolet visible (UV-Vis) spectroscopy	58
2.9	Physical observation of polymeric materials	63
CHAPTER 3 METHODOLOGY		66
3.1	Introduction	66
3.2	Methodology flow chart	67
3.3	Materials and apparatus/instruments	68
3.4	Preparation of biomonomer	69
3.5	Preparation of BP and BPC	70
3.6	Preparation of BP and BPC thin film for UV irradiation and tensile test	71
3.7	Fourier Transform Infrared Spectroscopy (FTIR)	75
3.8	Ultraviolet visible (UV-Vis) spectrophotometer	77
CHAPTER 4 RESULTS AND DISCUSSION		80
4.1	Introduction	80

4.2	Fourier transforms infrared (FTIR) study for monomer and biopolymer	80
4.2.1	Biomonomer (VOM and WOM) and biopolymer (VOP and WOP)	80
4.2.2	Non-UV irradiated and UV irradiated of BP and BPC of VOP at region 4000-650 cm^{-1}	85
4.3	Mechanical properties of BP and BPC upon UV irradiation	93
4.4	Carbonyl index (CI) and Hydroxyl index (HI) of BP and BPC upon UV irradiation	98
4.4.1	Carbonyl index (CI) of BP and BPC upon UV irradiation	98
4.4.2	Hydroxyl index (HI) of BP and BPC upon UV irradiation	101
4.5	UV-Vis study for BP and BPC of UV irradiated thin films	104
4.6	Physical properties of BP and BPC upon UV irradiation	109
CHAPTER 5 CONCLUSION AND RECOMMENDATION		113
5.1	Conclusion	113
5.2	Recommendation	115

REFERENCES	116
APPENDICES	128
VITA	143



PTTA UTHM
PERPUSTAKAAN TUNKU TUN AMINAH

LIST OF FIGURES

2.1	Schematic representations of three common classes of polymer structure	8
2.2	Various type of polymer structures	9
2.3	Stress influences on polymers	11
2.4	Effects of stress influences on polymers	11
2.5	Chemical structure of fats and oils	13
2.6	Hydrolysis reaction produces glycerol and fatty acids	13
2.7	Main fatty acids issued from vegetable and castor oil	14
2.8	Production (million tons and %) of nine major vegetables oil in 2013/14	15
2.9	Citation trend of (a) publications and (b) patents on bio-based polymers in recent years	16
2.10	Structures of pure MDI and polymeric MDI	18
2.11	Isomers of toluene diisocyanates	18
2.12	Chemical structure of TiO ₂	21
2.13	Mechanism of photodegradation	25
2.14	The chemical structures of HALS	37
2.15	The structures of some UV absorbers	38
2.16	Theory of antioxidant	40
2.17	Quinone retard oxidation process	40
2.18	Doping mechanism of nitrogen on titanium dioxide	43
2.19	The UV light spectrum and solar radiation	46
2.20	Correlation table for the infrared bands of polymers	50
2.21	FTIR-ATR spectra of chitin, polyurethane and chitin-	

polyurethane biocomposite	51
2.22 Typical FTIR spectra of PU coating before and after exposures for two different time intervals under the 300 nm cut-on filters in 50 °C/~0% relative humidity condition	53
2.23 FTIR spectra of chitosan before and after 13 hours of UV-irradiation	54
2.24 Tensile strength after different periods of weathering	57
2.25 The effect of exposure time on maximum elongation	58
2.26 UV-visible spectra of (a) unstabilized PET (b) with a detail on the region of 400 nm	59
2.27 Possible reactions leading to the formation of quinone and diquinone groups	60
2.28 UV-Vis spectrum for thin film (150-200 µm) of RS-PU	61
2.29 UV-Vis spectrum for thin film (150-200 µm) of SF-PU	61
2.30 Changes in UV-Vis spectra of chitosan/starch blends (75:25) after UV irradiation (0 - 13 hours)	62
2.31 UV-Vis absorption spectra (diffuse reflectance) of the original unimplanted pure TiO ₂ (a) and the Cr ion implanted TiO ₂ (b-d), and the solar spectrum which reaches the earth	63
2.32 Color change after QUV exposure for vinyl ester (VE), unsaturated polyester (UPE), unsaturated polyester-urethane hybrid (UPE hybrids) and polyurethane pultruded profiles (PU)	65
2.33 Colour changes, evident on displayed wood panels for water based acrylic coatings with stabilizer combinations and increasing concentrations of nanoparticles of anatase-B and rutile-A	65
3.1 Flow chart of methodology of BP and BPC	67
3.2 Instruments involve for characterization of BP and BPC	68



3.3	Waste cooking oil (WO) and virgin oil (VO)	69
3.4	Biomonomer mixed with MDI and TiO ₂ using mechanical stirrer	71
3.5	Biopolymer cast into a container	71
3.6	Measurement of dry-film thickness of BP and BPC using micrometer	72
3.7	The illustration of UV Accelerated Weatherometer	72
3.8	Biopolymer thin film samples on a rack for UV light exposure	73
3.9	The sample is mounted between two jaws of the tester and in line with the direction of pull	73
3.10	Schematic illustration of tensile test thin films polymer according to ASTM D882	75
3.11	Biopolymer as thin film sample for tensile test	75
3.12	FTIR spectrometer-Perkin Elmer	76
3.13	UV-Vis spectrophotometer - UNICO SQ-3802 model	77
3.14	Thin film sample for UV/Vis spectroscopy	78
3.15	Biopolymer thin films were fit into the 4-cell linear changer before testing	78
4.1	FTIR spectra at region 4000-650 cm ⁻¹ of VOM	81
4.2	FTIR spectra at region 4000-650 cm ⁻¹ of WOM	82
4.3	FTIR overlay spectra at region 4000-650 cm ⁻¹ of VOM (____) and WOM (_ _ _)	82
4.4	FTIR spectra at region 4000-650 cm ⁻¹ of VOP	83
4.5	FTIR spectra at region 4000-650 cm ⁻¹ of WOP	84
4.6	FTIR overlay spectra at region 4000-650 cm ⁻¹ of VOP (_ _ _ _) and WOP (____)	84
4.7	FTIR overlay spectra of non-UV irradiated and UV irradiated of BP and BPC of (a) VOP (b) VOP _{2.5} (c) VOP ₅ (d) VOP _{7.5} and (e) VOP ₁₀ at 250, 500, 750, 1000, 2000 and 3000 hours	88
4.8	FTIR overlay spectra of non-UV irradiated and UV irradiated of BP and BPC of (a) WOP (b) WOP _{2.5}	

(c) WOP ₅ (d) WOP _{7.5} and (e) WOP ₁₀ at 250, 500, 750, 1000, 2000 and 3000 hours	91
4.9 Mechanism of photo degradation of BP and BPC after UV irradiation	92
4.10 Average thickness for BP and BPC of (a) VOP and (b) WOP	93
4.11 Graph of tensile strength (MPa) against UV irradiation time for BP and BPC of VOP	94
4.12 Graph of tensile strength (MPa) against UV irradiation time of BP and BPC for WOP	96
4.13 Graph of elongation at break (%) against UV irradiation time (Hours) for BP and BPC of VOP	96
4.14 Graph of elongation at break (%) against UV irradiation time (Hours) for BP and BPC of WOP	97
4.15 Carbonyl index (CI) for non-UV irradiated and UV irradiated BP and BPC of VOP at 250, 500, 750, 1000, 2000, and 3000 hours	99
4.16 Carbonyl index (CI) non-UV irradiated and UV irradiated BP and BPC of WOP at 250, 500, 750, 1000, 2000, and 3000 hours	100
4.17 Hydroxyl index (HI) for non-UV irradiated and UV irradiated BP and BPC of VOP at 250, 500, 750, 1000, 2000, and 3000 hours	102
4.18 Hydroxyl index (HI) for non-UV irradiated and UV irradiated BP and BPC of WOP at 250, 500, 750, 1000, 2000, and 3000 hours to UV light	103
4.19 UV-Vis overlay spectra of absorbance for BP and BPC of (a) VOP (b) VOP _{2.5} (c) VOP ₅ (d) VOP _{7.5} and (e) VOP ₁₀	106
4.20 UV-Vis overlay spectra of absorbance for BP and BPC of (a) WOP (b) WOP _{2.5} (c) WOP ₅ (d) WOP _{7.5} and (e) WOP ₁₀	108



- 4.21 Yellowing changes of colour with extended UV irradiation time for BP and BPC of VOP; (a) non-UV irradiated and UV irradiated (b) 250, (c) 500, (d) 750, (e) 1000, (f) 2000, and (g) 3000 hours 110
- 4.22 Yellowing changes of colour with extended UV irradiation time for BP and BPC of WOP; (a) non-UV irradiated and UV irradiated (b) 250, (c) 500, (d) 750, (e) 1000, (f) 2000, and (g) 3000 hours 111



PTTHM
PERPUSTAKAAN TUNKU TUN AMINAH

LIST OF TABLE

2.1	Properties of titanium dioxide, TiO_2	20
2.2	Properties of anatase and rutile	21
2.3	Various research on the TiO_2 photocatalyst	23
2.4	Various research on the polymer stabilization	36
2.5	Three ranges of solar UV radiation spectrum	46
2.6	Study on the sample preparation and UV irradiation for polymeric materials	48
2.7	Typical tensile strength for polymer	56
2.8	Correlation between wavelength, colour, and complementary colour	58
3.1	BP and BPC of VOP and WOP doped with different percentage of TiO_2	70

LIST OF SYMBOL AND ABBREVIATIONS

<i>A/Abs</i>	-	Absorbance
<i>ASTM</i>	-	American Society for Testing Materials
<i>ATR</i>	-	Attenuated total reflection
<i>CO₂</i>	-	Carbon dioxide
<i>FTIR</i>	-	Fourier Transform Infrared
<i>H</i>	-	Hours
<i>MDI</i>	-	Methylene diisocyanate
<i>MPa</i>	-	Mega Pascal
<i>TiO₂</i>	-	Titanium dioxide
<i>%</i>	-	Percent
<i>eV</i>	-	1.6×10^{-19} Joule
λ	-	Wavelength
<i>nm</i>	-	Nanometer
μm	-	Micrometer
$^{\circ}\text{C}$	-	Degree Celsius
<i>BP</i>	-	Biopolymer
<i>BPC</i>	-	Biopolymer composite
<i>CI</i>	-	Carbonyl index
<i>HI</i>	-	Hydroxyl index
<i>UV</i>	-	Ultraviolet
<i>UV-Vis</i>	-	Ultraviolet visible
<i>VO</i>	-	Virgin oil
<i>VOM</i>	-	Virgin oil monomer

VOP - Virgin oil polymer
WO - Waste oil
WOM - Waste oil monomer
WOP - Waste oil polymer



PTTA UTHM
PERPUSTAKAAN TUNKU TUN AMINAH

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Presented paper	129
B	Chemical and apparatus	136
C	Experimental data	138



PTTA UTHM
PERPUSTAKAAN TUNKU TUN AMINAH

CHAPTER 1

INTRODUCTION

1.1 Introduction

In recent years, increasing interest in the development of more environment friendly polymer products such as plastics is observed. This trend has been spurred not only by the realization that the supply of fossil resources is inherently finite, but also by a growing concern for environmental issues, such as volatile organic solvent emissions and recycling or waste disposal problems at the end of a resin's economic lifetime. Furthermore, developments in organic chemistry and fundamental knowledge on the physics and chemistry of paints and coatings enabled some problems encountered in vegetable oil based products to be solved. This resulted in the development of coatings formulations with much improved performances that are based on renewable resources (Derksen *et al.*, 1996).

Palm oil is one of the most widely used plant oils in the world, which is grown in mass plantation in tropical countries. The competitive environment of the industry provides the drive needed to develop plastic materials that utilize less expensive material. Palm oil differs from its major competitors (soybean, sunflower seed, and rapeseed oil) in that it is obtained from a perennial tree crop and drought impacts are less severe in comparison to oilseed crops. Palm oil which contains significant amount of saturated bonds that presumably contribute to the non-drying

property of the resin synthesized. The non-drying alkyds have made tremendous improvement in quality of nitrocellulose lacquers. Preparation of the alkyd resin from non-drying palm oil may expand the application of the oil in various areas as environment-friendly materials, because of its abundance and renewability. There is no study reported on the synthesis of alkyd resin based on palm oil so far. However, the use of petroleum based monomers in the manufacture of polymers is expected to decline in the coming years because of spiraling prices and the high rate of depletion of the stocks. This has inspired the technologists all over the world to investigate renewable natural materials as an alternate source of monomers for the polymer industry as substitute for the petroleum-based monomers to manufacture polymers (Issam and Cheun, 2009).

The evaluation of the resistance to weathering of materials can be done by direct weathering outdoors, but for most purposes it is more practical in economical and time consumption terms to assess material performance by exposed to artificial light sources that accelerate the degradation. Degradation of polymeric materials by exposure to solar radiation or light is referred to as photo-oxidation. It is a free radical process, progressing even at low temperatures by the combine action of light and oxygen. Thermal oxidation is always superimposed on photo-oxidation (Robinson *et al.*, 2011).

Under the action of sunlight, polymer materials undergo a series of oxidative reactions that lead to chemical degradation, with consequences like brittleness, loss of brightness, colour change, opacity and formation of surface cracks. Besides the reduction in molecular weight, a number of changes take place in the molecules during photodegradation with the formation of chemical groups like carbonyl, carboxylic acids and hydroperoxides (Rabek, 1995).

Products like fibres and films tend to deteriorate under UV exposure to UV light, resulting mainly in fragility and loss of transparency. The degradation and stabilization of some types of polymer, like polyethylene were extensively investigated throughout the years and hence the degradation mechanisms and their controlling factors are reasonably well established (Fechine *et al.*, 2002). The common polymers normally photo degrade are fairly well known, but various aspects of the mechanisms involve remain unclear. It is important to take into account very significant influence of compounding additives in modifying the chemical pathways,

which are pigments, extenders, photo stabilizers and thermal stabilizers (Al-Shammary, 2011).

Normally polymers such as plastics are susceptible to auto-oxidation initiated by heat or UV-light during processing or long term use. In order to prevent the degradation of polymers, much kind of stabilizers have been developed and are now use widely in many applications. Normally for coloured materials, combination of UV absorbers and light stabilizer are used to achieve a measure of protection and prevent photo-oxidation (Gugumus, 1993). The aim of this study was to investigate the effect of UV stabilizers on the photodegradation of biopolymer composite. Film samples were exposed in the UV weatherometer and tested for mechanical properties and physical changes.

1.2 Background of study

Great interest towards biobased polymer in various applications is due to limited resources of petroleum based polymers and increased environmental concern. The development of novel feedstocks for polyurethanes derived from renewable materials has become important because the use of polyurethane polymers is increasing at a rate of 1 million tonnes a year. The reaction of organic isocyanate with compounds containing OH (hydroxyl) groups is capable of wide application in polymer formation. Thus the urethane linkage, $-(NHCOO)-$ can be produced by reacting compounds containing active hydrogen atoms with isocyanate, where polymer formation can take place if the reagents are di- or polyfunctional.

In this study, virgin and waste monomer was converted into a biopolymer composite with low loading of filler. This filler is widely used as a white pigment because of its brightness, very high refractive index ($n = 2.4$), cheap and abundance. It is also an effective opacifier in powder form or as a pigment to provide whiteness and opacity to products such as paints, coating, plastics, paper, inks, foods and most toothpaste. Titanium dioxide (TiO_2) is a semiconductor, with a band gap of 3.1 eV for rutile and tends to lose oxygen and become sub-stoichiometric. TiO_2 shows relatively high reactivity and chemical stability under ultraviolet light ($\lambda < 387$ nm). TiO_2 of photostabilizer is non-toxic and chemically stable (Zaleska, 2008; Anika

Zafiah, 2008). The applications of metal oxide filler as polymer additives included superhydrophobic photocatalysis as self-clean coating and photovoltaic solar cell (Anika Zafiah, 2013).

The primary end-use markets are construction, furniture, packaging and automotive industrial. Automotive interior and under hood parts, electrical connectors and microwaveable containers are examples of applications requiring high temperature resistance.

1.3 Problem statement

Environmental pollution and destruction on a global scale have drawn attention to the vital need for totally new, safe and clean chemical technologies and processes, the most important challenge facing chemical scientists for the 21st century. A large amount of waste cooking oil has become an environmental issue around the world. The Energy Information Administration in the United States estimated that some 100 million gallons of waste cooking oil is produced per day in USA, where the average per capita waste cooking oil was reported to be 9 pounds (Radich, 2006). In the European countries, the total waste cooking oil production was approximately 700,000-1,000,000 tons/year (Kulkarni and Dalai, 2006).

Synthetic polymers are produced from petrochemicals that cost very expensive. It also can burden to the environmental because it non-degrade and harming wildlife when they are dispersed in nature. Management of such oils and fats pose a significant challenge because of their disposal problems and possible contamination of the water and land resources As large amounts of waste cooking oils are illegally dumped into rivers and landfills, causing environmental pollution, so the use of waste cooking oil to produce biomonomer as biopolymer substitute offers significant advantages because of the reduction in environmental pollution.

The potential of biodegradable polymers has been recognized for a long time since they could be an interesting way to overcome the limitation of the petrochemical resources in the future. The fossil fuel and gas could be partially replaced by green agricultural resources, which would also participate in the reduction of CO₂ emissions (Avareus and Pollet, 2012). Due to concerns over

sustainability, environmental issues and raw material costs, the use of renewable resources such as waste cooking oil is very attractive to industries. It is because it most valuable to develop as raw materials for biopolymer composite and offers great choice with biodegradability, clean, safer and it relatively low cost with acceptable mechanical properties and wide range of application such as in coating field.

Such varnishes, lacquers or paints are usually made of highly crosslinked polymers which must exhibit a great resistance to solar radiation, moisture, pollutants and chemicals in order to ensure a long lasting protection. By lowering the mobility of the polymer chains, the network structure reduces the extent of both the production of initiating species (cage effect) and the propagation step, thus making crosslinked polymers more resistant to photo-oxidation. The durability of organic coatings can be further enhanced by the addition of light stabilizers (Decker *et al.*, 1995).

Polymers, such as plastics and coatings, are susceptible to photodegradation initiated by heat or UV-light during processing or long-term use. In order to prevent the photodegradation of polymers, different types of stabilizers have been developed and are now used widely in many applications. With the increasing use of polymers in exterior applications, there seems to be a growing need for excellent UV stabilizers such as TiO₂ to protect polymers from photodegradation (Kikkawa, 1995).

1.4 Importance/significance of the study

Biodegradable polymer composites have been developed from natural oils like epoxidized palm oil that has been used as monomer for production of resins. These vegetable oils have their own particular advantages like they are renewable products derived from natural oils and fats and are more readily biodegradable than the corresponding products made from petroleum sources.

Polymeric materials are commonly used of long-lasting products such as engineering applications, packaging, catering, surgery and hygiene. These polymers bring a significant contribution to a sustainable development in view of the wider range of disposal options with minor environmental impact.

The used of metal oxide as stabilizer with bio polymer in a coating application such as paint is a major concern in this study as the use of TiO_2 give no harm to environment. The stability of the biopolymer composites were tested under UV light using accelerated weathering tester which equivalent to the real outdoor weather condition.

1.5 Objective of the study

The main objectives of this project are:

- (i) To prepare biopolymer (BP) and biopolymer composites (BPC) for mechanical properties determination; tensile of unirradiated and UV irradiated for degradation study.
- (ii) To study the influence of UV irradiation on physical properties of BP and BPC.

1.6 Scope of the study

In this study, biopolymer (BP) and biopolymer composite (BPC) produced based on monomer of virgin and waste cooking oil. Waste cooking oil was obtained from Small and Medium Industries (SMIs). These BP components were named based on the starting vegetables oil such as virgin oil polymer (VOP) and waste oil polymer (WOP). BPC samples were doped with 2.5, 5, 7.5 and 10 wt. % of Titanium Dioxide (TiO_2). These samples were exposed using UV weatherometer at 250, 500, 750, 1000, 2000, and 3000 hours. The effects of UV light on the properties of BP and BPC were determined by tensile test and visual inspection based on the colour changes of the thin films. Meanwhile, Fourier transforms infrared (FTIR) spectroscopy and UV-Vis spectroscopy were used to provide valuable information of functional groups which can be used to determine the photo degradation of the BP and the influence of TiO_2 on the biopolymer composite. In addition, UV-Vis spectrophotometer was used to obtain the absorption spectra of BP and BPC.

CHAPTER 2

LITERATURE REVIEW

2.1 Polymer

Polymer is materials that the molecular structure consists of one or more structural units (monomers) repeated any number of times (Fried, 2008). Homopolymer has only one kind of structural unit which is repeated, while a copolymer has two or more different structural units which are repeated (Oil and Colour Chemists Association Southern Africa, 2011).

A polymer, from the Greek *poly*, meaning “many”, and *meros* meaning “part” is a long molecule consisting of many small units (monomers) joined end to end. A polymer is analogous to a necklace made from many small beads (monomers). There are many types of polymers including synthetic and natural polymers. Certain polymer, such as proteins, cellulose, and silk, are found in nature which are produced by living organism, known as biopolymers, while many others, including polystyrene, polyethylene, and nylon are produced only by synthetic route (Mc Crum *et al.*, 2003; Wicks *et al.*, 2007).

Another common name for many synthetic polymers is plastic which comes from the Greek word "plastikos", suitable for moulding or shaping. Many objects in daily use from packing, wrapping, and building materials include half of all polymers are synthesized. Other uses include textiles, TV's, CD's, automobiles, and many other

REFERENCES

- ADMET, (1996-2013). *Material Testing System, Tensile Property Testing of Plastics*.
- Abadal, M., Cermak, R., Raab .M., Verney, V., Commereuc, S., & Fraise, F. (2006). Study on photodegradation of injection moulded (beta)-polypropylene. *Polymer Degradation Stability*, 91(3), 459-63.
- Affolter, S. (1999). Long-Term Behaviour of Thermoplastic Materials. *Appl. Sci. Technology*, 1-21.
- Al Ani, K. E. & Anabtawi, M. (2012). UV-Irradiation Effect on the Photodegradation of Plasticized Poly (*Ortho, Meta, and Para*-Fluorostyrene) Isomers in Solid Films, *International Journal of Chemistry*, 4(5), 62-84.
- Al Ani, K. E. and Ramadhan, A. E. (2010). Plasticization effect on the photodegradation of poly (4- chlorostyrene) and poly (4-bromostyrene) films. *Materials Sciences and Applications*, 1(4), 358-368.
- Allen, N. S. & McKellar, J. F. (1980). *Photo Chemistry of Dyed and Pigmented Polymer*. London: Applied-Science Publishers.
- Allen, N. S., Edge, M., Ortega, A., Liauw, C. M., Stratton, J., & McIntyre, R. B. (2002). Behaviour of nanoparticle (ultrafine) titanium dioxide pigments and stabilisers on the photooxidative stability of water based acrylic and isocyanate based acrylic coatings. *Polymer Degradation and Stability*, 78(2002), 467–478.

- Allen, N. S., Edge, M., Mourelatou, D., Wilkinson, A., Liauw, C. M., Parellada, M. D., (2003). Influence of ozone on styreneethylenebutylene styrene (SEBS) copolymer. *Polymer Degradation and Stability*, 79(2), 297-307.
- Allport, D., Gilbert, D., and Outterside, S. (2003). *MDI and TDI: Safety, Health and the Environment*. England: John Wiley & Sons, Ltd.
- Al-Shammary, Z. R. (2011). The effect of inorganic pigment on the tensile properties of polycarbonate irradiated with UV – light. *Iraqi Journal of Physics*, 9(16), 52-56.
- Andrady, A.L., Hamid, S.H., Huc, X. & Torikai A. (1998). Effects of increased solar ultraviolet radiation on materials. *Journal of Photochemistry and Photobiology B: Biology*, 46(1998), 96–103.
- Anika Zafiah, M. R. (2008). Degradation studies of polyurethanes based on vegetable oils, Part 2; Thermal degradation and materials properties. *Prog. React. Kinet. Mech.*, 34, 1-41.
- Anika Zafiah, M. R. (2009). Material properties of novelty polyurethane based on vegetable oils. *The 11th International Conference on QiR (Quality in Research)*, Depok, Indonesia.
- Anika Zafiah, M. R. (2009). Effect of titanium dioxide on material properties for renewable rapeseed and sunflower polyurethane. *International Journal of Integrated Engineering*, 1(1), 15-20.
- Anika Zafiah, M. R. (2009). Degradation studies of polyurethanes based on vegetables oils, Part I; Photodegradation. *Prog. in React. Kinet. Mech.*, 33 (2008), 363-391.
- Anika Zafiah, M. R. (2010). Polymer from renewable materials. *Science Progress*, 93(3), 285-300.
- Anika Zafiah, M. R., Mohid, S. R., & Shaiqah, M. R. (2014.) Influence of N₂ and H₂O on UV Irradiated Bio Polymer Composite, *International Review of Mechanical Engineering (IREME)*, 8(1), 271-276.
- Anpo, M. (2000). Utilization of TiO₂ photocatalysts in green chemistry. *Pure Appl. Chem.*, 72(7), 1265–1270.
- Anpo, M. and Takeuchi, M. (2001). Design and development of second-generation titanium oxide photocatalysts to better our environment—approaches in realizing the use of visible light. *International Journal of Photoenergy*, 3 (2001), 89-94.

- Arana, J. (2002). TiO₂ - photocatalysis as a tertiary treatment of naturally treated wastewater. *Catalyst Today*, 76, 279.
- ASTM-D5154-91 (2000). Standard test method for determining the activity and selectivity of fluid catalytic cracking (FCC) catalysts by microactivity test (withdrawn 2000).
- ASTM-D 4587 (2012). Standard *practice for fluorescent UV-condensation exposures of paint and related coatings*.
- ASTM-D1005-95 -Reapproved 2007 (2012). *Standard Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers*.
- ASTM-D882-10 (2012). *Standard Test Method for Tensile Properties of Thin Plastic Sheeting*.
- Avérous, L and Pollet, E. (2012). *Environmental Silicate Nano-Biocomposites, Green Energy and Technology*. Verlag, London: Springer.
- Babu, R. P., O'Connor, K. and Seeram, R. (2013). Current Progress on bio-based polymers and their future trends. *Progress in Biomaterials*, 2(8), 1-16.
- Bajer, D. and Kaczmarek, H. (2010). Study of the Influence on UV Radiation on Biodegradable Blends Based on Chitosan and Starch. *Progress on Chemistry and Application of Chitin and its Derivatives*, Volume XV, 17-24.
- Baljit, S., and Nisha, S. (2008). Mechanistic implications of plastic degradation. *Polymer Degradation and Stability*, 93, 561-584.
- Baranwal, K. (2003). Mechanochemical degradation of an EPDM polymer. *Journal Applied Polymer Sciences*, 12(6), 1459-69.
- Bhargava, R., Wang, S., & Koenig, J. L. (2003). FTIR Microspectroscopy of polymeric systems. *Advances in Polymer Science*, 163, 137-191.
- Bottino, F. A., Cinquegrani, A. R., Giovanna, D. D., Leonardi, L., Antnino, P. A. (2004). Study on chemical modification, mechanical properties and surface photooxidation of films of polystyrene stabilized by hinderd amines (HAS), *Polymer Testing*. 23, 779-789.
- Bousted, I. (2005). Tolylene diisocyanates (TDI), Brussels, Belgium: Plastics Europe, Association of Plastics Manufacturer.
- Charles, H. A. (2000). *Modern Plastic Handbook*. New York: McGraw Hill Company.

- Chattopadhyay, D. K. and Raju, K .V. S. N. (2007). Structural engineering of polyurethane coatings for high performance applications. *Progress Polymer Science*, 32, 352–41.
- Chaudhari, S., Shaikh, T., and Pandey, P. (2013). A Review on Polymer TiO₂ Nanocomposites. *International Journal of Engineering Research and Applications*. 3(5), 1386-1391.
- Che, S. W. T. (2012). *Using Bio-Based Materials in the Automotive Industry*. University of Windsor: Master's Thesis.
- Cheremision, N. P. (1997). *Hand Book of Engineering Polymeric Materials*, Chapter 8. New York.
- Connolly, M., King, J., Shidaker, T., & Duncan, A. (2006). *Characterization of Pultruded Polyurethane Composites: Environmental Exposure and Component Assembly Testing*. Composites 2006 Convention and Trade Show, American Composites Manufacturers Association on October 18-20, 2006
- Davis, A. and Sims, D. (1983). Weathering of Polymers. *Applied Science Publishers*, 22(7), 294.
- Davila-Rodriguez, J. L., Escobar-Barríos, V. A., Shirai, K. & Rangel-Mendez, J. R. (2009). Synthesis of a chitin-based biocomposite for water treatment: Optimization for fluoride removal. *Journal of Fluorine Chemistry*, 130(8), 718-726.
- Decker, C., Biry, S. & Zahouily, K. (1995). Photostabilisation of organic coatings. *Polymer Degradation and Stability*, 49(1995), 111-119.
- Derksen, J. T. P., Cuperus, F., & Kolster, P. P. (1996). Renewable resources in coatings technology: a review, *Progress in Organic Coatings*, 27, 45-53.
- Diebold, U. (2002). Structure and properties of TiO₂ surfaces: a brief review. *Applied Physics A*, 76, 1-7.
- Duka, E. (2008). *Mechanical characterisation of very thin films*. Physics of Advanced Materials Winter School. Tirana University, Albania.
- Escobar Barríos, V. A., Rangel Méndez, J. R., Pérez Aguilar, N. V., Espinosa, G. A. and Dávila Rodríguez, J. L. (2012). *FTIR - An Essential Characterization Technique for Polymeric Materials, Infrared Spectroscopy Materials Science, Engineering and Technology*, Prof. Theophanides Theophile (Ed.), ISBN: 978-953-51-0537-4, InTech.

- Fechine, G. M., Rabello, M. S. & Souto-Maior, R. M. (2002). The Effect of ultraviolet stabilizers on photodegradation of poly (Ethylene Terephthalate). *Polymer Degradation and Stability*, 75(1), 153-159.
- Fechine, G. J. M., Rabello, M. S., Souto Maior, R. M., & Catalani, L. H. (2004). Surface characterization of photodegraded poly(ethylene terephthalate): The effect of ultraviolet absorbers. *Polymer*, 45(2004) 2303–2308.
- Feng, L. (2006). Preparation and Characterization of Polymer TiO₂ Nanocomposites via *In-situ* Polymerization. University of Waterloo, Ontario, Canada: Master Thesis.
- Fried, J. R. (2008). *Polymer Science and Technology*. New Jersey, United State: Prentice Hall.
- Fujishima, A. (2000). Titanium dioxide photocatalysis. *J. Photochem. Photobiol. C: Photochem. Rev.*, 1(2000), 1.
- Garforth, A., Fiddy, S., Lin, Y. H., Ghanbari-Siakali, A., Sharratt, P. N., and Dwyer, J. (1997). Catalytic degradation of high density polyethylene: an evaluation of mesoporous and microporous catalysts using thermal analysis. *Thermochim Acta*, 294, 65-9.
- Gesenhues, U. (2000). Influence of titanium dioxide pigments on the photodegradation of poly(vinyl chloride). *Polymer Degradation and Stability*, 68(2000), 185-196.
- Gilding, D. K. (1981). *Biodegradable polymers*. In: Williams, D. F, editor. Biocompatibility of clinic implant materials, vol. II. Boca Raton, FL: CRC Press.
- Givoni, B., and Hoffman, M. E. (1968). Effect of Building Materials on Internal Temperatures, *Research Report*, Building Research Station, Technion Haifa.
- Grassie, N. & Scott, G. (1985). *Polymer degradation and stabilization*. New York, NY: Cambridge University Press.
- Gugumus, F. (1993). Re-evaluation of the stabilization mechanisms of various light stabilizer classes. *Polymer Degradation Stability*, 39, 117-135.
- Guner, F. S., Yagci, Y., and Erciyes, A. T. (2006): Polymers from Triglyceride Oils. *Progress Polymer Science*, 31, 633–670.
- Haida International Equipment Ltd. (2013). *Environmental testing machine*. Operational manual.

- Hamid, S. H., Amin, M. B., & Maadhah, A. G. (1995). *Weathering degradation of polyethylene*. Handbook of polymer degradation. New York: Marcel Dekker.
- Hanaor, D. A. H. and Sorrell, C. C. (2011). Review of the anatase to rutile phase transformation. *Journal Material Science*, 46(2011), 855–874.
- Hergenrother, R. W., Wabers, H. D., and Cooper, S. L. (1992). The effect of chain extenders and stabilizers on the in-vivo stability of polyurethanes. *Journal Applied Biomaterial*, 3, 17-22.
- International Standard Organization (2013). *Plastics Methods of exposure to laboratory light sources: Part 3-Flourescent UV lamps*. (ISO 4892-3: 2013).
- Issam, A. M. and Cheun C. Y. (2009). A Study of the Effect of Palm Oil on the Properties of a New Alkyd Resin. *Malaysian Polymer Journal*, 4(1), 42-49.
- Kaczmarek, H. and Podgorski, A. (2007). Photochemical and thermal behaviors of poly (Vinyl alcohol) graphite oxide composite. *Polymer Degradation and Stability*, 92(6), 939-946.
- Kiatkamjornwong, S., Thakeow, P., and Sonsuk, M. (2001). Chemical modification of cassava starch for degradable polyethylene sheets. *Polymer Degradation and Stability*, 73, 363-75.
- Kikkawa, K. (1995). New developments in polymer photostabilization. *Polymer Degradation and Stability*, 49, 135-143.
- Kobayashi, M. and Kalriess, W. (1997). Photocatalytic Activity of Titanium Dioxide and Zinc Oxide: The effect of organic and inorganic surface treatments. *Cosmetics and Toiletries Magazine*, 112, 83-85.
- Krebs, C., and Avondet, M.A. (1999). *Long term Behaviour of Thermoplastics – Ageing Behaviour and Chemical Resistance*, Hanser-Verlag München; German.
- Kulkarni, M. G. and Dalai, A. K. (2006). Waste Cooking Oils an Economical Source for Biodiesel: A Review. *Ind. Eng. Chem. Res.* 45, 2901-2913.
- Li J, Guo S, and Li X. (2006). Degradation kinetics of polystyrene and EPDM melts under ultrasonic irradiation. *Polymer Degradation and Stability*, 89(1), 6-14.
- Liu Y. (2000). *New Biodegradable polymers from Renewable resources*, Department of polymer Technology, Royal institute of Technology, Stockholm; Sweeden.
- Liu, M., Horrocks, A. R. & Hall, M. E. (1995). Correlation of physicochemical changes in UV-exposed low density polyethylene films containing various UV stabilizers. *Polymer Degradation Stabilization*, 49(1), 151-161.

- Lu, J., Deshpande, S. V., E. Gulari, Kanickia, J., and Warren, W. L. (1996). Ultraviolet light induced changes in polyimide liquid-crystal alignment films. *Journal Applied Physics*, 80(9), 5028-5034.
- Lundin, T, Cramer, S. M., Falk, R. H., & Felton, C. (2004). Weathering of natural fiber filled polyethylene composites. *Journal Material Civil Engineering*, 16(6):547-55.
- Maissel, L. I. and Glang, R. (1970). *Handbook of Thin Film Technology*. International Business Machines Corporation Components Division. Hopewell Junction N.Y: East Fishkill Facility.
- Marcilla, A., Gomez, A., Menargues, S., Garcia-Martinez, J., and Cazorla-Amoros, D. (2003). Catalytic cracking of ethylene vinyl acetate copolymers: comparison of different zeolites. *J. Anal. Appl. Pyrolysis*, 68-69, 495-506.
- Mark, H. F., Bikales, N. M., Overberger, C. G. & Menges, G. (1986). *Encyclopedia of polymer science and engineering*. 2nd ed., vol. 4. New York: Wiley Interscience Publication.
- Martin, J. W., Chin, J. W., and Nguyen, T. (2003). Reciprocity law experiments in polymeric photodegradation: a critical review. *Progress Organic Coatings*, 47, 292-311.
- Mat Taib, R., Ahmad Zauzi, N. S., Mohd Ishak, Z. A., & Rozman, H. D. (2010). Effects of Photo-Stabilizers on the Properties of Recycled High-Density Polyethylene (HDPE)/Wood Flour (WF) Composites Exposed to Natural Weathering. *Malaysian Polymer Journal*, 5(2), 193-203.
- Mc Crum, N. G., Buckley, C. P. and Bucknall, C. B. (2003). *Principle of Polymer Engineering*, Great Clarendon Street: Oxford University Press Inc.
- McKeen, L. W. (2013) *The effect of UV light and weather on plastics and elastomers*. 3rd edition, Elsevier, William Andrew. UK.
- Mohid, S. R., Anika Zafiah, M. R., Nurulsaidatulsyida, S., & Marsi, N. (2013). Biopolymer Doped with Titanium Dioxide Superhydrophobic Photocatalysis as Self-Clean Coating for Lightweight Composite, *Advances in Materials Science and Engineering*, Hindawi Publishing Corporation.
- Mohid, S. R., Anika Zafiah, M. R., Nurulsaidatulsyida, S., Talib, D. A. and Tuan Ya, T. M. Y. S. (2013). Mechanical properties of UV irradiated bio polymer thin films doped with titanium dioxide. *Advanced Materials Research*, 748(2013), 165-169.

- Mukherjee, D. (2011). *Development of a Novel TiO₂-polymeric Film Photocatalyst for Water Purification both under UV and Solar Illuminations*. The University of Western Ontario: Ph.D. Thesis.
- Nagai, Y., Ogawa, T., Nishimoto, Y. & Ohishi, F. (1999). Analysis of weathering of a thermoplastic polyester elastomer II. Factors affecting weathering of a polyetherepolyester elastomer. *Polymer Degradation Stability*, 65(1999), 217-224.
- Nakamura, H., Nakamura, T., Noguchi, T., Imagawa, K. (2006). Photodegradation of PEEK sheets under tensile stress. *Polymer Degradation and Stability*, 91(4), 740-746.
- Narine, S. S. and Kong, X. (2005). *Vegetable Oils in Production of Polymers and Plastics*. Bailey's Industrial Oil and Fat Products. Sixth Edition. John Wiley & Sons.
- Nguyen, T., Martin, J. W., Byrd, E. & Embree, E. (2002). *Effects of Spectral UV on Degradation of Acrylic-Urethane Coatings*. Proceedings of the 80th Annual Meeting of the Program of the FSCT, Federation of Societies for Coatings Technology, October 30-November 1, 2002, New Orleans, LA.
- Nik Yusuf, N. A. A. (2011). *Bio, Thermal and Photo Degradation of Thin Films from Renewable Resources*. Universiti Tun Hussein Onn Malaysia: Master's Thesis.
- Oil and Colour Chemists Association Southern Africa (2011). *Encyclopedia of Terms and Definitions used in the Surface Coating Industry*.
- Palmisano, A. C. and Pettigrew, C. A. (1992). Biodegradability of plastics. *Bioscience*, 42(9), 680-5.
- Pandey, J. K., Reddy, K. R., Kumar, A. P., Singh R. P. (2005). An overview on the degradability of polymer nanocomposites. *Polymer Degradation and Stability*, 88, 234-250.
- Peacock, A. J. and Calhoun, A. (2006). *Polymer Chemistry: Properties and Applications*. Carl Hanser Verlag, Munich: Hanser Gardner Publications, Inc.
- Petrović, Z. S. (2008). Polyurethanes from Vegetable Oils. *Polymer Reviews*, 48, 109–155.
- Pielichowski, K. and Njuguna, J. (2005). *Thermal Degradation of Polymeric Materials*, Rapra Technology Limited, the Printing house, Crewe, UK.

- Pospisil J, and Nespurek, S. (2000). Addcon World 2006. *Progress Polymer Science*, 25, 1261-1335
- Rabek, J. F. (1995). *Polymer Photodegradation. Mechanisms and Experimental Methods*. London: Chapman and Hall.
- Radich, A. (2006). Biodiesel performance, costs, and use. US Energy Information Administration.
- Ramis, X., Cadenato, A., Salla, J. M., Morancho, J. M., Valles, A., and Contat, L. (2004). Thermal degradation of polypropylene/starch-based materials with enhanced biodegradability. *Polymer Degradation and Stability*, 86, 483-91.
- Ranby, B. and Rabek, J. F. (1975). *Photodegradation, Photooxidation and photostabilization of polymers*. New York: Wiley Interscience Publications.
- Reich, L. and Stivala, S. S. (1971). *Elements of polymer degradation*. New York: McGraw-Hill Book Company.
- Robinson, J., Linder, A., Gemmel, A., Poulsen, K. V., Burkhard, H., Hogstrom, P. A., Kobilsek, M. (2011). Comparison of standard UV test methods for the ageing of cables. . *Proceedings of the 60th IWCS Conference*. Charlotte Convention Centre: International Wire and Cable Symposium. pp. 329-337
- Saleh, N. J. and Shnean, Z. Y. (2009). A Study the Effect of UV Light on Pigmented and Unpigmented LDPE. *Engineering & Technology Journal*, 27(4), 706-716.
- Salem, M. A. (2001). Mechanical Properties of UV- Irradiated LDPE Films Formulated with Carbon black and Titanium Dioxide. *Egypt, J. Sol.*, 24(2), 141-150.
- Sandler, S. R., Karo, W., Bonesteel, J. and Pearce, E. M. (2002). *Polymer Synthesis and Characterization: A Laboratory Manual*. Elsevier.
- Sawyer, L. C., Grubb, D. T., & Meyers, G. F. (2008). *Polymer Microscopy* (3rd. edition). Verlag Berlin Heidelberg, Germany: Springer.
- Saw, P. Y., Hui, Y. T., and Sudesh, K. (2006). Photocatalytic activity and biodegradation of polyhydroxybutyrate films containing titanium dioxide. *Polymer Degradation and Stability*, 91(2006), 1800-1807.
- Scalarone, D., Lazzari, M., Oscar Chiantore, O. (2012). Acrylic protective coatings modified with titanium dioxide nanoparticles: Comparative study of stability under irradiation. *Polymer Degradation and Stability*, 97(2012), 2136-2142.

- Sekine, Y., and Fujimoto, K., (2003). Catalytic degradation of PP with an Fe/activated carbon catalyst. *J Mater Cycl Waste Manag.*, 5, 107-12.
- Selvin, T. P., Kuruvilla, J. and Sabu, T. (2003). Mechanical properties of titanium dioxide-filled polystyrene microcomposites. *Materials Letter*, 58(2004), 281-289.
- Semsarzadeh, M. A. and Salehi, H. (2000). Autoxidation of polypropylene glycol and its catalysis with ferric acetylacetonate. *European Polymer Journal*, 36, 1001-1010.
- Shakashiri, (2008). Fats and Oils, *Chemical of the Week*, General chemistry.
- Sheldrick, G. E. and Vogl, O. (2004). Induced photodegradation of styrene polymers: a survey. *Journal Polymer Engineering Science*, 16(2), 65-73.
- Sionkowska, A., Płancka, A., Lewandowska, K., Kaczmarek, B., & Szarszewska P. (2013). Influence of UV-Irradiation on Molecular Weight of Chitosan. *Progress on Chemistry and Application of Chitin and Its Derivatives*, Volume XVIII, 21-28
- Singh, B. and Sharma, N. (2007). Mechanistic implications of plastic degradation. *Polymer Degradation and Stability*, 93(2008), 561-584.
- Siwinska, D., Kołodziejczak-Radzimska, A., Krysztafkiewicz, A., & Jesionowski, T. (2009). Adsorption of octylamine on titanium dioxide. *Applied Surface Science*. 255, 7337-7342.
- Smith, R., Williams, D. F., and Oliver, C. (1987). The biodegradation of poly(ether urethanes). *J. Biomed. Mater. Res.*, 21, 1149-66.
- Srichatrapimuk, V.W. and S. Cooper (1978). Infrared thermal analysis of polyurethane block polymers. *J. Macromol. Sci., Phys. B*, 15(2), 267-311.
- Stuart, B. H. (2004). *Polymer analysis*. England: John Wiley & Sons, Ltd.
- Stuart, B. H. (2004). *Infrared Spectroscopy: Fundamentals and Applications*. England: John Wiley and Sons, Ltd.
- Suresh, S. N., Kong, X., Bouzidi, L., and Sporns, P. (2007). Physical Properties of Polyurethanes Produced from Polyols from Seed Oils: II. Foams. *J Amer Oil Chem Soc*, 84, 65-72.
- Temple, C. P. (1973). *Pigment Hand Book: Applications and Markets, Vol. II*. New York: John Wiley and Sons.

- Tham, K. W. and Willem, H. C. (2010). Room air temperature affects occupants' physiology, perceptions and mental alertness. *Building and Environment*, 45, 40–44.
- The American Society for testing and materials (ASTM) methods, ASTM book of standards; (2005) 08.03, Plastics (III): D5117.
- Tschan, M. J. L., Brule, E., Haquette, P. and Thomas, C. M. (2012). Synthesis of biodegradable polymers from renewable resources. *Polymer chemistry*, 3, 836-851.
- United State Department of Agriculture (USDA) (2014). *Table 47: World vegetable oils supply and distribution 2009/10 - 2013/14*, Data Products, Oil Crops Yearbook.
- United State Environmental Protection Agency (EPA) (2011). *Methylene diphenyl diisocyanate (MDI) and related compounds action plan*. RIN 2070 -ZA15.
- Van de Velde, K. and Kiekens, P. (2002). Biopolymers: overview of several properties and consequences on their applications. *Polymer Testing*, 21, 433–442.
- Vazquez, M. and Hanslmeier, A. (2006). *Ultraviolet radiation in the Solar System*. Netherlands: Springer.
- Verhoeven, J. W. (1996). Glossary of Term Used in Photochemistry. *Pure & Appl. Chem.*, 68(12), 2223-2286.
- Wall, L. L., Madorsky, S. L., Brown, D. W., and Straus, S. (1954). The depolymerization of polymethylene and polyethylene. *J. Am. Chem. Soc.*, 76, 3430-7.
- White, K. R. and Shyichuk, A. V. (2007). Effect of stabilization on scission and cross-linking rate changes during photo-oxidation of polypropylene. *Polymer Degradation and Stability*, 92(11) 2095-2101.
- Wicks, Z. W., Jones, F. N., Pappas, S. P. & Wicks, D. A. (2007). *Organic Coatings: Science and Technology*, Wiley Publishing.
- Willis, .P. B. (1984). Investigation of test method material properties and processes for solar cell in capsulation, eighth annual report.
- Wojciechowski, K., Skowera, E., Pietniewicz E., Zukowska, G. Z., Van der Ven, L. G. J., Korczagin, I., Malanowski, P. (2014). UV stability of polymeric binder films used in waterborne facade paints. *Progress in Organic Coatings*, 77, 298-304.

- Wypych, G. and Faulkner, T. (1999). *Weathering of Plastics, Plastics Design Library*. New York: William Andrew Applied Science Publisher.
- Xu, C., Bradley, L. K., Robert, S., Sarah, H. T., and Vijay, G. (2009). Tensile Testing of Thin Films Supported on Compliant Substrates. *Mechanics of Materials* 41, 839–848.
- Yildiz, Y., Kizilcan, N., Uyanik, N. (2006). Effects of Acetophenone-formaldehyde Resin on The Degradation of High-Density Polyethylene by UV-irradiation. *Pigment & Resin Technology*, 35(5), 247–251.
- Young, R. J. (1987). *Introduction to Polymers*. Chapman & Hall. ISBN 0-412-22170-5.
- Yousif, E. (2010). *Photostabilization of PVC by inorganic complexes*. Germany: Lambert Academic Publishing.
- Yousif, E., Salimon, J., and Salih, N. (2011). *Photostability of poly (vinyl chloride)*. VDM Verlag: Dr. Muller publisher.
- Yousif, E. (2012). *Photostabilization of thermoplastic polymers*. Germany: Lambert Academic Publishing.
- Yousif, E., Salimon, J., and Salih, N., (2012). New stabilizer for polystyrene based on 2-Thioacetic Acid Benzothiazol complexes. *Journal of applied polymer Science*, 125, 1922-1927.
- Yousif, E. and Haddad, R. (2013). Photodegradation and photostabilization of polymers, especially polystyrene: review. *SpringerOpen Journal*, 2, 398.
- Yousif, E., Salimon, J., and Salih, N. (2014). Mechanism of photostabilization of poly(methy methacrylate) films by 2-thioacetic acid. *Arabian Journal of Chemistry*, 7, 306–311.
- Yu, C. T., Xian, H. H., Han, Q. Y. and Li, H. T. (2012). Nitrogen-doped TiO₂ photocatalyst prepared by mechanochemical method: Doping mechanism and visible photoactivity of pollutant degradation. *International Journal of Photoenergy*, 10, 1155.
- Zaleska, A. (2008). Doped-TiO₂: A Review. *Recent Patents on Engineering*, 2(3), 157-164.
- Zhang, Z., Hu X. and Luo, Z. (1999). Wavelength sensitivity of photo-oxidation of polypropylene. *Polymer Degradation and Stability*, 51(1), 93-97.
- Zweifel, H. (2000). *Plastics Additive Handbook*, 5th Ed. Germany: Hanser-Verlag München.