

2 DIMENSION WOVEN KENAF UNSATURATED POLYESTER COMPOSITE

MOHD PAHMI BIN SAIMAN

A thesis submitted in
fulfilment of the requirement for the award of the
Doctor of Philosophy

Faculty of Mechanical and Manufacturing Engineering
Universiti Tun Hussein Onn Malaysia

AUGUST 2014

ABSTRACT

In recent years, natural fiber from vegetables such as hemp, sisal, ramie, jute and kenaf has been recognized and studied by many researchers due to its potential as an alternative material for synthetic fibers in composite application. Kenaf fiber is a potential reinforced material for composite due to its acceptable properties and supported by the development in Malaysian Kenaf cultivation. Previous studies have demonstrated that Kenaf fibers were recognized in several applications such as automotive component, panel board, packaging, filter material and industrial paper. However, the reinforcement of the fibers is in random, unidirectional and particle form. Therefore, this research is focusing on the composites woven structural preform from the kenaf fiber assisted with the use of internal geometry modeling for optimization. The effect of primary parameters, which are the yarns properties, the fabric count and the weave designs were evaluated on its physical and mechanical properties. Different woven design preform (plain, twill 4/4, satin 8/3 and basket 4/4) were fabricated using floor loom and infused with unsaturated polyester resin using vacuum infusion process. The mechanical properties of the composites were measured and showed that satin 8/3 has highest tensile strength of 39MPa and Plain has highest tensile modulus of 2.63GPa, with flexural strength and impact strength of 48MPa and 29kJ/m² respectively. The use of VIP and UPE show a good infusion of resin between intra yarns but need much lower viscosity on the UPE for inter yarns. The use of 5% sodium hydroxide solution with the application of tension during the treatment enhanced the composite strength of 12%. The stacking sequence and orientation of 0°,45°,0° of the laminate composite had increased the flexural strength and impact strength of 73MPa and of 82MPa respectively. It is recommended to use a plain and satin structure for better infusion in vacuum infusion process.

ABSTRAK

Beberapa tahun kebelakangan ini, serat semulajadi dari tumbuhan seperti hemp, sisal, rami, jut dan kenaf telah diiktiraf dan menjadi bahan kajian oleh ramai penyelidik kerana kemampuannya sebagai bahan alternatif serat sintetik dalam aplikasi komposit. Serat kenaf merupakan bahan berpotensi untuk digunakan sebagai pengukuh komposit kerana sifatnya yang boleh diterima dan disokong oleh pembangunan penanaman Kenaf di Malaysia. Kajian terdahulu menunjukkan serat kenaf dikenali dalam beberapa aplikasi seperti komponen automotif, papan panel, pembungkusan, bahan penapis dan kertas industri. Namun begitu, serat pengukuh berbentuk rawak, satu arah, dan partikal. Oleh itu, kajian ini memberi tumpuan kepada prabentuk struktur tenunan kering daripada serat kenaf dibantu dengan penggunaan pemodelan geometri dalaman sebagai pengoptimuman. Kesan parameter utama iaitu sifat yan, ketumpatan fabrik dan rekaan tenun dinilai pada sifat fizikal dan mekanikal. Rekaan tenunan berbeza (plain, twill4/4, satin8/3 dan basket4/4) dihasilkan menggunakan mesin tenun lantai dan melalui pengisian resin poliester tak tepu menggunakan proses infusi vakum. Sifat mekanikal komposit dinilai dan didapati satin 8/3 mempunyai kekuatan tegangan pada 39MPa dan Plain mempunyai modulus tegangan 2.63GPa, kekuatan lenturan pada 48MPa dan kekuatan impak pada 29kJ/m². Penggunaan proses infusi vakum menunjukkan infusi yang baik diantara yan tetapi memerlukan poliester tak tepu yang lebih rendah kelikatannya untuk antara serat. Penggunaan larutan 5% sodium hidroksida dengan aplikasi tegangan semasa rawatan meningkatkan kekuatan komposit sebanyak 12%. Urutan susunan dan orientasi 0°,45°,0° komposit lamina dapat meningkatkan kekuatan lenturan dan kekuatan impak masing-masing pada 73MPa dan 82MPa. Adalah dicadangkan untuk menggunakan struktur plain dan satin untuk infusi yang lebih baik menggunakan kaedah proses infusi vakum.

TABLE OF CONTENTS

DECLARATION OF THESIS STATUS	
EXAMINERS' DECLARATION	
TITLE	i
STUDENT'S DECLARATION	ii
DEDICATION	iii
ACKNOWLEDGEMENT	iv
ABSTRACT	v
TABLE OF CONTENTS	vii
LIST OF TABLE	xii
LIST OF FIGURE	xiv
LIST OF SYMBOLS AND ABBREVIATIONS	xix
LIST OF APPENDICES	xxi
CHAPTER 1 INTRODUCTION	1
1.1 Background of study	1
1.2 Problem statement	3
1.3 Objectives	5
1.4 Scope and limitations	5
CHAPTER 2 LITERATURE REVIEW	6
2.1 Introduction	6
2.2 Polymer matrix composite	
2.3 Natural fibers	10
2.3.1 Kenaf bast fibers	11
2.3.2 The properties of Kenaf fibers	13
2.3.3 The fiber's surface modification	15

2.3.4	Kenaf fibers in polymer composites	16
2.4	Textile composite	17
2.4.1	2D woven perform	20
2.4.2	Weaving structure	22
2.5	Geometry modeling for woven textile	27
2.6	Application of unsaturated as polymer matrix	30
2.7	Vacuum infusion process	31
2.8	Summary of literature	32

CHAPTER 3 METHODOLOGY **34**

3.1	Introduction	34
3.2	Internal geometry modeling for 2D woven Kenaf perform	35
3.2.1	Fibre and yarn input data internal geometry model	39
3.2.2	Weave design input data for internal geometry model	42
3.2.3	Fabric count input data for internal geometry model	43
3.3	Experimental materials and their properties	45
3.4	Sample preparation	46
3.4.1	Preparation of 2D woven preform	46
3.4.2	Alkali treatment	50
3.4.2.1	Exposing single fibre with 6%NOH solution	51
3.4.2.2	Alkali treatment on woven Kenaf	51
3.4.2.3	Application of tension on woven dry preform	51
3.4.3	Preparation for laminate composite	53
3.5	Vacuum infusion process (VIP) set-up and equipment	54

3.6	Testing procedure and equipment	57
3.6.1	Tensile properties	57
3.6.2	Flexural properties	58
3.6.3	Impact properties	60
3.6.4	Fracture surface morphology and structure	61
CHAPTER 4 RESULT AND DISCUSSION		62
4.1	Introduction	62
4.2	Internal geometry of 2D woven kenaf modelling	63
4.2.1	Kenaf yarn's geometrical structure	66
4.2.2	Weave design simulation using 3D image	66
4.2.3	Simulation of yarns per cm for fabric count	69
4.2.4	Simulation of preform properties	70
4.3	2D woven preform samples	72
4.4	Comparison between prediction and experimental dry perform	75
4.5	2D woven kenaf reinforced unsaturated polyester composite	78
4.5.1	Effect of fibre loading	78
4.5.1.1	Optimizing fabric count	79
4.5.1.2	Effect of yarn linear density on physical properties	81
4.5.1.3	Effect of yarn linear density on tensile properties	82
4.5.1.4	Effect of yarn linear density on flexural strength	85
4.5.1.5	Effect of yarn linear density on impact strength	86
4.5.2	Weave design on 2D woven kenaf unsaturated polyester composite	90

4.5.2.1	Effect of weave design on tensile strength	91
4.5.2.2	Effect of weave design on flexural strength	94
4.5.2.3	Effect of weave design on impact strength	95
4.5.3	Surface treatment	98
4.5.3.1	Effect of alkali treatment on reinforced materials	99
4.5.3.2	Effect of alkali treatment on composite tensile properties	101
4.5.3.3	Effect of alkali treatment on flexural strength	104
4.5.3.4	Effect of alkali treatment on impact strength	105
4.5.4	Laminate composite	109
4.5.4.1	Effect of laminate stacking angle on tensile strength	110
4.5.4.2	Effect of laminate stacking angle on flexural strength	112
4.5.4.3	Effect of laminate stacking angle on impact strength	114
4.5.4.4	Comparison between mechanical properties of single layers composite with laminate composite	117
4.6	Comparison with different natural based composites	119
CHAPTER 5 CONCLUSION AND RECOMENDATION		122
5.1	Conclusion	122
5.2	Recommendation	123
REFERENCES		124
APPENDIX		140

LIST OF TABLES

2.1	Comparison between Thermosetting and Thermoplastic matrix	8
2.2	Advantages and disadvantages of kenaf fibres	14
2.3	Examples of Linear Density and Yarn Numbering System	21
2.4	Two different levels of textile reinforced preform	28
3.1	General and mechanical properties of Kenaf fibers as input data in a geometrical model	39
3.2	Kenaf yarn properties of three different linear densities based on input data in geometrical model	41
3.3	Yarns properties selected for woven sample	45
3.4	Characteristics of the Unsaturated Polyester resin	46
4.1	Prediction of Kenaf yarn properties	65
4.2	Selection of geometrical model for weave designs	66
4.3	Selection of geometrical model for fabric count	70
4.4	Selection of weave design for experimental according to geometric properties and in-plane deformation	71
4.5	Specifications of actual woven plain dry preform for three different yarn linear densities	72
4.6	Actual specifications of selected preform weave	74

	design for 759tex yarn	
4.7	Comparison between prediction and experimental data	76
4.8	Comparison between different fabric counts and dry preform properties	79
4.9	Physical properties of reinforced plain weave for three different yarn tex	82
4.10	Percentage expansion of Kenaf fiber and 759tex composite	100
4.11	Properties of 276tex and 759tex of laminate composites	110
4.12	Comparison of Properties for different natural based composite	121



LIST OF FIGURES

2.1	Classification of PMC composites	7
2.2	Common processes in Composite Fabrication	9
2.3	Classification of natural fibres	10
2.4	The condition of Kenaf beginning from plant, stem and fibres	12
2.5	Comparison of different natural fibres and E-Glass	14
2.6	Textile preform for composite materials	18
2.7	Interlacement of warp yarn and weft yarn according to the preform design	20
2.8	Schematic diagram of shuttle loom weaving machine	22
2.9	Examples of designs of Composite Reinforcing Materials (a) Twill 2/2 (b) Sateen	23
2.10	Examples of modified and complex design weave	23
2.11	The waviness of warp yarn crimp	25
2.12	Diagram of the parameters affecting woven textile composite	27
2.13	Multi level simulation approach	29
2.14	Example of tensile test simulation for two-layered polyester preform	29
3.1	Flowchart of research methodology	36

3.2	Data input Flowchart for building up the 2D woven Kenaf geometry model	38
3.3	SDL Electric Twist Tester Y220B	40
3.4	Diameter of the yarn in a compressed and flattened state	40
3.5	The “Tension Curve” for 276tex, 413tex and 759tex of yarns as input data in geometrical model	42
3.6	The 2D weaves structure for checking and validation	43
3.7	The difference between yarn spacing and yarn per cm	44
3.8	Tension in warp and weft direction and shear angle	44
3.9	Kenaf yarn used in weaving process	47
3.10	Draw-in process for Kenaf warp yarn	47
3.11	Weave plan of Plain 1/1 design for 759tex	48
3.12	Floor loom	48
3.13	Ammes fabric thickness gauge	49
3.14	Test sample with standard dimension for strip method	50
3.15	Stretching technique on the dry woven preform before submerge in a 6%NaOH solution	52
3.16	Ply angle and preform stacking	53
3.17	A diagram showing all parts of VIP	55
3.18	The preparation of VIP parts before infusion	55
3.19	A full set of VIP ready to be infused	56
3.20	Resin flow distributed on the VIP system from resin tank	57
3.21	The specifications of the tensile test specimen	58

3.22	Characteristics of the specimen and the position of the equipment	59
3.23	Position of test specimen and striker after the impact	60
3.25	The SHIMADZU Hydroshot Impact Test Machine	61
4.1	The geometry of yarn cross section and fibre distribution in yarn	63
4.2	The “Tension rigidity” of 276tex, 413tex and 759tex of yarns as input data in geometrical model	66
4.3	A woven plain dry perform and images of three different linear densities under microscope of 7X magnification	72
4.4	2D woven preform sample with 3D image (a) Twill 4/4 (b) Satin 8/3 (c) Basket 4/4	74
4.5	Comparison of tensile force between predicted and actual dry woven perform	78
4.6	Comparison between different fabric counts	80
4.7	Example of composite panel	81
4.8	Cross sectional view of composites for three different linear densities under a microscope at 7× magnification	82
4.9	Tensile strength of composites for different yarn linear densities	83
4.10	Young’s modulus for composite of different linear densities	84
4.11	SEM images of composites with three different yarn linear densities	85
4.12	Flexural strength of different linear densities	86
4.13	Composite panel after impact test with front and back face	87

4.14	Impact strength of different linear densities	88
4.15	Energy vs. Time of composites under impact of 10m per sec	89
4.16	Force vs. Stroke of composites under impact of 10m per sec	90
4.17	Composite plat of selected weave	91
4.18	Relationship between yarn crimp percentage, preform tensile force and composite tensile strength in warp direction with different weave designs	92
4.19	Comparison between microscopic image of Basket 4/4 and Satin 8/3 composite before and after tensile test	93
4.20	Weaved cross section of Basket 4/4 the showing jammed structure	94
4.21	Flexural strength of different weave design composites	95
4.22	Impact strength of different weave design composites	96
4.23	Impact damage on front face and back face of composite panels	97
4.24	Force-Stroke response of different weave composites	98
4.25	Kenaf single fibre under optic microscope of 35× magnification; (a) Original diameter of Kenaf fibre (b) Diameter changes in Kenaf fibre after exposed to 6% NaOH	99
4.26	Chemical reaction after alkali treatment	100
4.27	Composite under microscope at 7× magnification	101
4.28	Tensile strength of different composites	102
4.29	Young's modulus of different composites	102

4.30	SEM of treated and stretch-treated composites	103
4.31	Flexural strength of untreated, treated and stretch-treated composites	105
4.32	Impact strength of untreated, treated and stretch-treated composite	106
4.33	Composite panel after impact test with front and back face	107
4.34	Energy-Stroke responses of different untreated, treated and stretch-treated composites	108
4.35	Force-Stroke responses of different untreated, treated and stretch-treated composites	109
4.36	Example of laminate composite with stacking angle $45^{\circ}0^{\circ}45^{\circ}$	109
4.37	Tensile strength of 276tex and 759tex woven kenaf laminate composites	111
4.38	Young's Modulus of 276tex and 759tex woven kenaf laminate composite	112
4.39	Flexural strength of 276tex and 759tex woven kenaf laminate composite	113
4.40	Composite panel after impact test with front and back face	114
4.41	Effect of stacking sequence on the impact strength of 276tex and 759tex laminate composites	117
4.42	Comparison between maximum properties of single layer and laminate composite	119

LIST OF SYMBOLS AND ABBREVIATIONS

2D	-	2 dimension
d	-	Diameter
V_f	-	Fibre volume fraction
N_f	-	Numbers of fibers
W_{t_f}	-	Weight fibre fraction
f_{wa}	-	The number of warp intersections
f_{we}	-	The number of weft intersections
L, l	-	Length
P	-	Actual length of the yarn
n	-	Fabric ply number in the composite
m	-	Areal density
ρ	-	Density
h	-	Thickness
P	-	Tension curve
F_x	-	Force acting in warp direction
F_y	-	Force acting in weft direction
γ	-	Shear angle
N_e	-	English cotton count
NaOH	-	Natrium hydroxide
MEKP	-	Methyl ethyl ketone peroxide
FRP	-	Fibre reinforced polymer
LCM	-	Liquid composite moulding
UPE	-	Unsaturated polyester
VIP	-	Vacuum Infusion Process
VOC	-	Volatile organic compounds

RTM	-	Resin transfer moulding
SEM	-	Scanning Electron Microscope
ASTM	-	American Society for Testing and Materials
CSM	-	Chopped strand mat



LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Article in proceedings; The Effect of Compression Temperature and Time on 2D Woven Kenaf Fiber Reinforced Acrylonitrile Butadiene Styrene (ABS)	140
B	Article in proceedings; The Effect of Yarn Linear Density on Mechanical Properties of Plain Woven Kenaf Reinforced Unsaturated Polyester Composite	147
C	Article in proceedings; The Effect of Fabric Design on Woven Kenaf Reinforced Unsaturated Polyester Composite using Vacuum Infusion Process	154



CHAPTER 1

INTRODUCTION

1.1 Background of study

Currently, the use of natural based composite has significant potential for positive environment outcome. Conventional synthetic materials are excellent for their physical and mechanical properties but these fibres have serious drawbacks such as not being non-renewable, non-recyclable, high energy consumption during the manufacturing process, health risk and non-biodegradable [1]. Due to these issues, the composite industry consisting of natural based composites began to show concern when green advantages (renewability and biodegradability) of natural based composites became an important criteria and top-end mechanical properties were not the primary motivation [2]. Although natural fibres can be used as a green substitute, properties like low density are known for its suitability for use in lightweight structures. In most cases, natural fibres are cheaper compared to synthetic fibres and pose less health problems. Therefore, the interest in the use of natural fibres as reinforcement for polymeric matrix composite has attracted attention from the engineering, automotive and consumer sectors.

Generally, there is a broad range of natural fibres that mainly originate from vegetable, animal and mineral fibres. Most fibres that are considered natural fibre composites are vegetables bast fibres that have inherit good mechanical properties due to its cells or groups of cells that are designed for strength and stiffness [3]. This includes the Kenaf bast fibre, which is an annual crop that is native to Africa. It has been identified as a potential alternative crop to be grown in Malaysia due to its

industrial value and this would have an economic impact on farmers. Traditionally, Kenaf fibers were used in products, such as ropes, twine and burlap but studies have shown that it is capable of being an industrial material. At present, most of the Kenaf fibres produced are reinforced material for composites that are in form of random short fibres. It is well known as a raw material in fibre reinforced polymer composites and is already adopted as automobile parts due to its lightweight and mechanical properties [4]. However, there is no indication that the emphasis on structural reinforced material has been highlighted.

A structural reinforced material in composite can be classified as a 2Dimensional (2D) and 3Dimensional (3D) textile preform. It can be defined through the in-plane thickness where 2D preform is a single layer thickness while 3D is discrete layers stacked at a desired thickness with interlock system. However, at the moment 2D is more demanding due to its low cost production. A 2D woven Kenaf as a structural reinforced material for natural based composites in its area of study has yet to be explored although some work on natural fibres such as flax [5], hemp [6-8] and jute [5-9] have already been published. The application of 2D woven is a structural reinforcement with bidirectional orientation to provide greater strength and stiffness depending on the fabric architecture [10]. Traditionally, the woven structural composites were used in high-end applications such as aerospace, automotive, energy and civil constructions. These structural woven composites have potential demand due to the material's greater stiffness and strength yet being lighter in the field. The construction of the woven structure has gained attention as it offers flexible designs with greater advantage during fabrication and performances. The fabrication with polymers using different processing techniques generates different properties for the suitability of application. Reports indicate that some of the properties have shown to be comparable or even better than glass fibres such as; specific modulus [11], energy production [6, 12], low cost [13] and processing flexibility [14].

The development of 2D woven Kenaf composite can be seen as an attempt to decrease the dependence on synthetic fibres in composites and increase the usability of kenaf-based products. This leads to the need for investigations on the structural architecture of the dry preform and fabrication technique to optimize the performance of the composite.

1.2 Problem statement

In order to prepare natural fibres as engineering materials for composites, many researchers have attempted different kinds of techniques. Natural fibres can be produced as reinforced material in different ways such as particle, randomly oriented fibres, structural, laminate, etc. There have been previous studies on Kenaf fibres, particularly in form of random fibres and unidirectional [4, 15-18]. Composites made from random fibres have strengths in all possible directions but not as strong or as stiff as unidirectional or bidirectional woven reinforced composites [19]. When in the form of unidirectional structure, the strength is characterised in one direction but weak in the transverse direction. In order to gain balanced mechanical properties, the structural woven composite is found to have advantages in terms of mechanical properties in biaxial way.

However, to produce a woven fabric made from natural fibre to be used as reinforcement materials and matching it with polymer matrix involves the consideration of several basic concepts. Many studies on the structurally natural based woven composites have neglected the basic formation of the reinforced structure that would affect the mechanical and physical properties of the composites. The studies had focused on the fibres while ignoring the basis of the structure such as the fabric count, yarn linear density and weave design. This is important as the structure of the woven itself has its own weakness such as the waviness of yarn crimps or the degree of bending occurring due to the interlacement between yarns. Hence, higher crimp produces stiffer fabrics with poor drapeability and reduces the fibre's load bearing capability [20].

Therefore, the emphasis on the structural formation of the dry fabric or dry preform will determine the ability towards the processing methods, the effectiveness of the matrix and the composite itself. The processing method such as hand lay-up, compression and closed mould have been used in the fabrication of natural based composite. However, the condition of the twisted continuous strand in a biaxial weave preform require well-suited matrix material and processing methods to produce a good composite This is important as it involves in the wetting process, impregnation and penetration between inter and intra yarn. Information on it was not well established in previous studies.

In addition, Kenaf fibres or *lignocellulosics* are agro-based materials that contain cellulose, hemicelluloses and lignin and it needs adaptation to make it compatible with the process of making composites. Therefore, due to its native properties, the typical problems are the lack of good interfacial adhesion, low degradation temperature and poor resistance towards moisture that makes it less attractive than synthetic fibre, which has been up until now the only choice for reinforcing polymeric composites due to their superior mechanical properties [6]. Previous studies have shown significant improvement in the mechanical properties as shown in the treatment of random fibres. This could indicate that there are several techniques that can be used to improve the properties of a Kenaf woven composite.

Several investigators have used different kinds of technique in structural composite to enhance the mechanical properties of the composites and one of it is laminate technique. It is a popular technique due to their low cost, high strength and stiffness to density ratio [21]. Applying it in structural composite depends on several factors such as fibers, matrix and the interface [22]. Others factors may influence on the properties are the stacking sequence and the angles which might increase or decrease the mechanical properties of the composites. However, the suitability to apply it in kenaf structural reinforced material needs to be studied.

Therefore, from the best of the author's knowledge, no study has reported on 2D woven Kenaf composites in terms of structure and the processing technique. Therefore, this study is focusing on the parameters of the 2D woven kenaf structure formation with different design processing techniques to enhance the mechanical properties of the composite.

1.3 Objectives

The aim of the research is to develop a composite made from 2D woven kenaf fibres impregnated with unsaturated polyester using the Vacuum Infusion Process (VIP). This will be completed with the following objectives:

1. To investigate the dry woven Kenaf preform primary parameters (yarn linear densities, fabric count and weave design) using internal geometrical modelling.
2. To investigate the fabrication method using unsaturated polyester impregnated with Vacuum Infusion Process (VIP).
3. To analyse and evaluate the effect of woven design parameters using sodium hydroxide treatment and stacking sequence on the mechanical properties of composites using the experimental method.

1.4 Scope and limitations

The scope of the study is to develop a natural-based composite in the form of a structurally reinforced woven polymer matrix. The study will include the use of internal geometric modelling software to predict and analyse the dry fabric and the composite. The experiment will focus on the processing method in the fabrication of naturally based woven fabrics with polymer matrix to gain the results in terms of mechanical properties. The study involves kenaf fibres with unsaturated polyester resin and infused into a composite using vacuum infusion. The experiment will look at the woven fabric structure, treatment and laminating composites in identifying the mechanical properties.

CHAPTER 2

LITERATURE REVIEW

2.1 Introduction

This chapter introduces and elaborates the background of composites, especially focusing on reinforced fibres, polymer matrix and the use natural fibres as reinforced material. The emphasis was given towards kenaf fibres, focusing on the properties and the development in the area of natural based composites. Certain techniques were introduced in this chapter related to the enhancement of mechanical properties against the dry preform and composite. The selection of the polymer resin and the appropriate processing method has been described based on the relevance of the composite fabrication.

2.2 Polymer matrix composites

Polymer matrix composite (PMC) is a composite consisting of a polymer thermoplastic or thermosetting reinforced by fibres [23]. The reinforced material provides the mechanical and physical properties as a load barrier. The matrix plays the role of protecting the fibres against environmental degradation and mechanical damage, but the main purpose is to hold the fibres together and transfer the loads on it.

PMC can be classified according to the geometry of the reinforcement or by the use of matrix materials as illustrated in Figure 2.1. The form of reinforcement and the arrangement usually shows anisotropy properties (directionally dependent)

because of the distinctive properties of the constituents and the non-homogeneous or textured distribution of the reinforcement. However, it can be isotropic when the reinforcement becomes smaller in size and randomly oriented [20]. PMC can further sub-divide according to the matrix, which is thermoplastic and thermosetting. Commonly, the main difference between thermoplastic and thermosetting is that thermoplastic can be re-melted and recycled. Thermosetting polymer is typically cured and moulded into shaped which is difficult to be recycled.




Figure 2.1: Classification of PMC composites [24].

The properties of fibre reinforced polymer (FRP) composite are usually compared based on the mechanical properties of strength and stiffness. The high strength and stiffness of the reinforced fibres make them desirable materials for use in many applications [25]. Apart from the transfer matrix to reinforcement, the strength and stiffness has also been determined along fibre direction and transverses the fibre direction [20]. Nevertheless, the matrix properties can also be considered as

it determines the resistance of the composites that may cause the failure of the structure. Table 2.1 shows the general characteristics of the polymer matrix. However, failure or fracture during servicing might occur, which is affected by the following variables: (a) type of fibre and fibre assembly construction; (b) type of matrix; (c) fibre-matrix interfacial bond strength and toughness; (d) fibre orientation and ply stacking sequence; (e) presence of flaws or discontinuities; (f) mode and rate of loading, and (g) environment (heat, moisture, chemicals) [26].

Table 2.1: Comparison between Thermosetting and Thermoplastic matrix [27].

Resin Type	Process temperature	Process time	Use temperature	Solvent resistance	Toughness
Thermoset Toughened Thermoset Lightly cross linked Thermoplastic Thermoplastic	Low ↑ High	High ↓ Low	High ↑ Low	High ↓ Low	Low ↑ High

The typical applications of FRP are desired due to the specific strength (strength to weight ratio) and specific stiffness (stiffness to weight ratio) of the composites. It is proven to be adaptable as engineering materials for application in sectors such as automotive, civil, electrical and electronic, marine, transportation, consumer products, etc. The most widely used FRP is glass fibre reinforced polymer (GFRP), while the less common types are carbon and aramid fibres, which are subjected to the cost range between fibres. The major resin polymer matrix is unsaturated polyester, which has good mechanical properties with acceptable cost and when more mechanical properties are needed, epoxy is preferable with a higher cost [28]. The fabrication techniques employed by the FRP industry are illustrated in Figure 2.2 and shows two different types of factor. First, is the type of polymer matrix, which is both a thermosetting or thermoplastic polymer and the second factor is the type of reinforced fibre, either a short or long fibre. The process will determine the performance of the composite, even though the focus is on the reinforcing materials. For example, study on the processing method between compression moulding and twin screw extrusion process on glass fibres reinforced with wood/PVC composites shows compression moulding has better mechanical

properties because of lower shearing stress [29]. A comparison between wet lay-up with autoclave consolidation and resin transfer moulding (RTM) by vacuum impregnation to fabricate glass fibre epoxy composites shows different fibre fractions where autoclave is much higher due to higher compaction resulting in better mechanical properties [30].

Undoubtedly, synthetic fibres are dominant in FRP composites, especially GFRP but over the last few years, a good deal of work has been dedicated to natural fibres with the hope of replacing synthetic fibres. This is truly important as a step towards finding a solution for environmental sustainability. Since some technical issues of natural fibres seem to be barriers towards becoming replacement fibres, the art of improvement embraces the architecture and the processing method is indispensable.




Figure 2.2: Common processes in Composite Fabrication [31].

2.3 Natural fibres

In recent years, owing to the increased environmental awareness, the use of natural fibres as a potential replacement for synthetic fibres such as carbon, aramid and glass fibres in composite materials has gained interest among researchers [32]. Enhanced with the issues of over rising costs, unstable supply and negative environmental impact of fossil fuels, the use of natural fibres is being vigorously promoted.

Natural fibres are classified (Figure 2.3) according to their source, which are animal, vegetable or mineral. There are many types of natural fibres being investigated but most of them come from vegetables due to its properties. Vegetable fibres from seeds, bast, leaf and fruits are common forms of fibres and are expected to replace the traditional synthetic fibres. The most common fibres used are flax, hemp, jute, wood, rice husk, wheat, barley, cane (sugar and bamboo), grass, kenaf, ramie, sisal, coir, kapok, banana fibres and pineapple leaf fibres. These fibres are usually used as the reinforcement in the development of natural based composites.





Figure 2.3: Classification of natural fibres.

The advantage of natural fibres over other established materials are that it is environmentally friendly, fully biodegradable, abundantly available, renewable and cheap and has a low density [33-35]. Furthermore, properties such as being lightweight, of reasonable strength and stiffness make it a material of choice when replacing synthetic fibres [36]. Even though, natural fibres look like promising materials, there are a few drawbacks to be considered. According to Mallick [37], among the disadvantages of natural fibres are its low tensile strength compared to traditional fibres such as E-glass and carbon fibres. It also has a low decomposition temperature and a tendency to absorb moisture. At temperatures higher than 200°C, most natural fibres start to degrade, which leads to odour, discoloration, release of volatiles, and deterioration of mechanical properties. Besides, it also has poor adhesion between natural fibres and the polymer matrix due to the hydrophilic nature of plant fibres and the hydrophobic of the matrix.

However, the disadvantage of low tensile strength of plant fibre is balanced by its low density, making it high in strength per weight ratio. Low decomposition temperature of plant fibre occurs during processing and most of the processes are below 200°C, which makes it acceptable. The tendency of poor adhesion between fibres and matrix has led towards various studies. This has led to several varieties of treatment to increase the compatibility between the fibre and matrix such as the use of coupling agents and alkali treatment. Nevertheless, there is more to be explored before it is steadily being used as a preferred reinforcing material.

2.3.1 Kenaf bast fibers

Kenaf fibre as shown in Figure 2.4 is an agricultural crop extracted from the Kenaf's bast (*Hibiscus Cannabinus*, L; family *Malvaceae*) as a potential fibre for industrial applications. Kenaf originates from Africa and is mainly grown in South-east Asia. It grows so fast that as many as three harvests a year are possible and it is an environmental friendly crop as 1 ha of kenaf cultivated area can absorb about 30-40 tons of CO₂, during one cultivation cycle [38].



Kenaf plant

Kenaf stem



Kenaf long fibers

Figure 2.4: The condition of Kenaf beginning from plant, stem and fibers.

In the Malaysian scenario, the development of Kenaf started during early 2000, beginning with research and development (R&D) by the Malaysian Agricultural Research and Development Institute (MARDI) and other academic sectors and government agencies. Since then, the Malaysian government has spent more than RM48 million for research in Kenaf cultivation and utilization [39]. This has been accelerated with the government's agenda on the development of Kenaf cultivation as an alternative crop for tobacco. Furthermore, the National Tobacco Board (LTN) was restructured and named the National Kenaf and Tobacco Board (LKTN). There are indications that Kenaf can grow in several areas in Malaysia and


in 2004 and 2005 the area cultivated by Kenaf was 42.2 hectares and in 2007 it grew to 700 hectares [40]. With the development of Kenaf cultivation, it is necessary to diversify the use of Kenaf, especially in industrial applications.

2.3.2 The Properties of Kenaf fibres

Kenaf has a high fibre yield, consisting of an inner core fibre (75–60%) and an outer bast fibre (25–40%) [41]. The long bast fibres are usually used in the production of high grade pulp in the pulp and paper industry, protective packaging for fruits and vegetables, filters, composite boards and textiles [42]. Kenaf comprises three principle chemical constituents, which are cellulose, hemicelluloses and lignin. The content of cellulose is 60-80%, lignin is 5-20% and moisture is 20% [43]. The strength and stiffness of the fibres are provided by cellulose components via hydrogen bonds and other linkages. The cellulose is highly crystalline, thus making it resistant to chemical attacks and degradation. Hemicellulose is physically a white solid material with rare crystalline or fibrous matter, which is in a form of flesh that fills out the fibre. It is responsible for biodegradation, moisture absorption, and thermal degradation of the fibre. On the other hand, lignin (pectin) is thermally stable, but responsible for the UV degradation of the fibres. The structure of lignin is intended as a binder to hold the fibre together and as a stiffening agent within the fibres [42, 44].

Traditionally, Kenaf fibres were used as a cordage crop to produce twine, rope, gunny-sacks and sackcloth [36]. The Kenaf's bast fibre was expanded into a new market of mouldable, nonwoven fabric and reinforced composite materials in automotive, aerospace, packaging and other industrial applications. The interesting part of Kenaf fibre is in its properties such as low cost, lightweight, renewable, biodegradable and highly specific mechanical properties. It has superior flexural strength and excellent tensile strength that makes kenaf a good candidate for many applications [15]. However, kenaf is at the middle range compared to other natural fibres in terms of strength, specific strength, stiffness and specific stiffness as shown in Figure 2.5. It also has its advantages and disadvantages which is comprised of natural fibres as being mentioned in Table 2.2.

a) Strength and specific strength



b) Stiffness and specific stiffness




Figure 2.5: Comparison of different natural fibres and E-Glass.

Table 2.2: Advantages and disadvantages of kenaf fibres [46].

Advantages	Disadvantages
<p>Low specific weight resulting in a higher specific strength and stiffness than glass.</p> <p>Renewable resources, production require little energy and low CO₂ emission.</p> <p>Production with low investment at low cost.</p> <p>Friendly processing, no wear of tools and no skin irritation.</p> <p>High electrical resistant.</p> <p>Good thermal and acoustic insulating properties.</p> <p>Biodegradable.</p> <p>Thermal recycling is possible.</p>	<p>Lower strength especially affects strength.</p> <p>Variable quality, influence by weather.</p> <p>Poor moisture resistant, which causes swelling of the fibre.</p> <p>Restricted maximum processing temperature.</p> <p>Lower durability.</p> <p>Poor fire resistant.</p> <p>Poor fibre/matrix adhesion.</p> <p>Price fluctuation by harvest results or agricultural politics.</p>

2.3.3 The fibre's surface modification

Kenaf fibers as reinforced polymer composites depend on several factors that affect its performance. These factors are the incompatibility between the hydrophilics of the fibre and the hydrophobic polymer matrices, the fibres content regarding tensile properties and the processing parameters which are affecting the properties and interfacial characteristics [34]. Kenaf fibres have high moisture absorption due to the large amount of the hydroxyl group in cellulose that gives it the hydrophilic properties. When it is used as a reinforcement combine with hydrophobic matrix the result is a very poor interface and poor resistance to moisture absorption [47]. Studies have shown that chemical modifications are usually used to optimize the interface of fibres.

There are several types of chemical modifications used on natural fibres to expedite the adhesion of natural fibres to the polymer matrix such as Alkaline Treatment, Silane Treatment, Acetylation of Natural Fibres, Benzoylation Treatment, Maleated Coupling Agents, Isocyanate Treatment, Permanganate Treatment and Acrylation and Acrylonitrile Grafting [48]. However, previous studies have shown that only a few chemical treatments were used on Kenaf fibres by researchers. The most widely used was the Alkali treatment, which is consisted of soaking the Kenaf fibres in a Sodium Hydroxide (NaOH) solution in a controlled temperature for a certain period of time and later rinsing it to remove any excess NaOH from the fibre's surfaces. The previous studies show that 5–6% by weight of NaOH was the optimum concentration under different temperature and soaking time [17, 38, 49]. The reason for using NaOH solution is to clean the fibre surface, chemically modify the surface, stop the moisture absorption process and increase the surface roughness [50]. This would subsequently increase the effectiveness of the fibre's surface area in adhering well with the matrix.

A study by Chao et al. [49] showed that an increase of tensile strength by Kenaf fibres when treated with 5% NaOH but there was no difference with Young's modulus and fracture strain. This shows that NaOH treatment will increase the strength of kenaf fibres and improve the compatibility between the fibres and matrix adhesion. However, there was also finding that show a decline of mechanical properties when using alkali treatment. El-Shekeil et al. [51] reported on the Kenaf

fiber-reinforced thermoplastic polyurethane (TPU/KF) composite fabricated with melt-blending method. The result shows the tensile, flexural and impact properties of untreated TPU/KF as superior compared to treated TPU/KF composite showing unsuitability for the composite. Apart from the use of individual alkali treatment, there were also reports showing a combination of alkalization with silane treatment. It was found that both treatments of alkali and silane offered superior mechanical properties compared to untreated fibre reinforced composite or individual treatment [52].

Still, previous reports have shown that most of the chemical modifications on Kenaf fibres are in the form of randomly oriented or fibre mats but not in structural formation. Therefore, it is interesting to evaluate the conditions of kenaf fibres that occur in the form of packing fibres twisted strands with structural interlacement of textile composite.

2.3.4 Kenaf fibres in polymer composites

Over the past few decades, interest in kenaf as a reinforced fibre for natural based composites had focused on the characteristics of kenaf fibres and the manufacturing process. Researchers more likely preferred random fibre orientation, compressed mat and prepeg versions. Most of the issues investigated dealt with the mechanical properties, thermal properties and moisture absorption using different kinds of polymer matrix and techniques.

Lee et al. [53] studied the effects of volume fraction on the mechanical properties on mixed and long discontinuous kenaf fibres with polypropylene (PP) using the carding and punching process. The result showed an increase of tensile and flexural modulus but it reached an optimum nominal fibre fraction of 30%. The result was similar with the findings of El-Shekeil et al. on Kenaf fibre-reinforced thermoplastic polyurethane (TPU/KF) composite fabrication using the melt-blending method [54]. Ochi used the prepeg method by placing emulsion-type PLA resin in the surface of unidirectional kenaf fibres and fabricated it using the hot press. It indicated stability of thermal properties in the PLA but found that the tensile strength of kenaf fibres decreased when kept at 180°C for 60min in moulding condition [16].

Rashdi et al. [15] did a study on a kenaf fibre and unsaturated polyester composite. The composite was tested in three different conditions; water immersion, soil buried and natural weather and was compared to dry kenaf fibres. The results showed that relative humidity (RH) was higher in the case of water immersion, and soil buried conditions, whereas in case of natural weather the effects of RH was slightly lower leading to high tensile strength. This has led to suggestions on kenaf as a candidate for outdoor application. Azrin et al. [55] studied woven composites consisting of coir and kenaf fibres in relation to its mechanical properties of impact and flexural. Woven composites were prepared using hand lay-up coupled with vacuum bagging. The results showed that woven coir composites displayed better mechanical properties compared to kenaf composites.

Even though there was a study on woven Kenaf reinforced composite, effect on the woven structure was not emphasized. Researchers are keen on random kenaf fibres, as the studies have shown some weaknesses with the composite, which are:

- i. Fibre breakage during processing especially in injection moulding.
- ii. Uncontrollable fibre orientation.
- iii. Uneven fibre dispersion making it ineffective in distributing loads from polymer to reinforced material.
- iv. Uncontrollable fibre loading.
- v. Low in drapeability, which causes difficulty during the moulding process.

Most of the drawbacks from random fibres can most likely be overcome using a structurally reinforced material. It is currently being used in synthetic fibre composites for industrial purposes and various other applications.

2.4 Textile composite

Textile composite materials consist of textile reinforcements with polymer matrix of either thermosetting or thermoplastic. The textile reinforcement material is in the form of interlaced structures consisting of yarns with various preform constructions such as woven, braided, knit or stitched [56-57]. Generally, the continuous fibres might be constructed in the form of preform that is randomly oriented, uniaxial or biaxial according to the technique and the properties concerned. It is one of the

promising technologies and its application in composites is tremendously increasing in various fields such as aerospace, marine, automotive, etc. [58].

Textile composites can be characterized by the formation of the reinforced materials as seen in Figure 2.6. The textile preform is separated into two different preforms consisting of 2-Dimensional (2-D) planar textile preform (single layer fabric) and 3-Dimensional (3-D) textile preform (multilayer interlock fabric). The 3-D preform has highly damage tolerance and impact resistance as the trend to delamination which been diminished due to the existence of reinforcements in the thickness direction [57]. However, it is less popular than 2-D since the making involving special mechanism and complex design. The woven preform is currently the most widely used with glass, carbon and aramid reinforced woven composites and in a wide variety of applications.




Figure 2.6: Textile preform for composite materials [59].

The advantages of textile composites are its low density, high strength, high stiffness to weight ratio, good chemical resistance, excellent durability, and design flexibility [60]. It is also found that the process of spinning has randomised fibre defects that is deleterious to fibre properties and gives rise to composite microstructural failure [61]. Even though it has various advantages but the main reason is ease of handling and low cost fabrication [62-63]. The textile reinforced materials can be manufactured in high production limits with advanced automated manufacturing systems that are being implemented by traditional fabric presently. The disadvantages of textile composite include lower fibre volume fraction, the existence of resin-rich volumes between yarns and degraded in-plane properties (as a result of the non-straight path that the yarns must accommodate) [64]. Studies also found that the introduction of twist during spinning has lead the reinforcement “off-axis” and thus not able to provide maximum reinforcement. The yarn crimp in the preform reduced the reinforcement efficiency and possible problems with poor resin penetration into the yarn [61]. Although there are some disadvantages, the textile reinforced composite is still acceptable in terms of properties, production cost and ease of production.

The mechanical properties of textile composites are controlled by two parameters, which are the textile preforms and laminate parameter [65-66]. The parameters for textile perform will be discuss in subtopic 2.4.2. A laminate composite is a number of layers or lamina and the orientation of the fibres depend on the application of the load direction. The parameters that influence the mechanical properties of laminate composites are usually the stacking orientation and overall fibre volume fraction, V_f . Hence, if the laminate is subjected only to an axial load that causes tension, the fibres in all layers should have the same orientation of the load in order to obtain the greatest possible strength. However, if the load is in a different direction, such as in a compression, it is more stable by positioning some of the layers of the fibres perpendicular to the load. Positioning some layers so that their fibres are oriented at 30° , 45° , or 60° to the load may also be used to increase the resistance of the laminate to the in-plane shear [67].

2.4.1 2D woven preform

The 2D woven preform can be defined as an interlacement of two set yarns known as warp yarn in the vertical axis and the weft yarn in the horizontal axis. It can be divided into three different fractions consisting of yarns that are single or a bundle of fibres, sets of yarns in preform and lastly the preform itself. The fibres are in form of continuous and discontinuous, which are called filament and staple or short fibres, either synthetic or natural and being twisted to strengthen the yarn. Figure 2.7 shows the interlacement of warp yarn and weft yarn with sectional view following the arrangement of weave design.

The yarn been determined according to linear density, which is the mass of a yarn per unit length and the inverse form, is called yarn numbering system or yarn count (Table 2.3). Spun yarn and natural fibres are impossible to be used in diameter as a dimension since it varies from point to point along the length making it weaker in strength [68]. The unevenness, or coefficient of variation of linear density for yarns made of short and stiff fibres such as flax, have an unevenness that can be as high as 15-20% [69]. If both yarns are being compare, the spun yarns tend to be hairy and fuller handled while filament yarns are more smooth and lustrous.




Figure 2.7: Interlacement of warp yarn and weft yarn according to the preform design.

Table 2.3: Examples of Linear Density and Yarn Count System.

Linear Density (Direct system)	Definition	Yarn Count (Indirect system)	Definition
Tex	No. of grams per kilometres	Metric Count (Nm)	No. of kilometres per kilograms
Decitex (dtex)	No. of grams per 10 kilometres	English Cotton Count (Ne)	No. of 840 yard hanks per pounds
Denier (Den)	No. of grams per 9 kilometres	Glass (UK and US, N_G)	No. of pounds per yards

The fabrication of textile structure for 2D woven preform in textile composites can be produced using modern weaving loom. Historically, the weaving machine starts from shuttle loom, where the picking system or the weft insertion system uses the shuttle (Figure 2.8). The development of textile has introduced the shuttle picking system, which is classified into four different types of systems; i) air-jet ii) water-jet iii) rapier and iv) projectile. This system operates under automated control, which makes the quality of the fabric much higher compared to the shuttle system and is able to produce several hundreds of kilograms per hour. The pattern controlling system is the heart of the weaving system and categorized into three different systems; i) cam ii) dobby and iii) jacquard. The cam system is the basic system and produce simple patterns usually for plain fabric. Meanwhile, the Dobby system produces patterns that are more complex but still has limitations and can only reach as many as 32 harnesses. The jacquard system can produce unlimited patterns but still depends on the capability of the weaving machine.




Figure 2.8: Schematic diagram of shuttle loom weaving machine.

2.4.2 Weaving structure

Weaving structure is a manner of construction or the arrangement of two set yarns determined by three main elements, namely the i) yarn properties in terms of thickness, surface characteristics, fibre content, strength, extensibility, etc. ii) fabric count or the density (threads per inch or per centimetre, and iii) weave design [70-71]. The manipulation of the elements will produce different mechanical properties, physical properties, chemical properties and the aesthetic value of the fabric.

The basic pattern of woven structure consists of plain, twill and satin or sateen weave. The plain weave is the simplest weave where the threads interlace in alternate order. The weave construction can be represented in a design paper consisting of square paper or checker board. Referring to Figure 2.7, the blank square indicates that the weft thread is placed over the warp and vice versa. The weaves are classified as balanced and unbalanced preform whereas balanced weave have the same linear density and fabric count for both warp and weft direction. Plain weave is the most highly interlaced preform that causes tightness and the most resistant to in-plane shear movement, sometimes it is difficult to wet out during densification. However, it can be relied on to give reproducible laminate thickness [71]. Plain

weave is usually used as a woven structure in textile composites for synthetic fibres such as glass and carbon fibres.

The twill order of interlacing as showed in Figure 2.9 (a), produces diagonal lines on the preform. The purpose is to make the preform heavier, with a closer setting and better draping. It is more pliable than plain weave and with better drapability and stability compared to the satin weave [72]. In pure sateen weaves, the surface of the preform consists almost entirely of weft floats. This has lessen the yarn crimps and improved the preform strength according to the function of a reinforcement materials in textile composites. It has a smooth surface with lots of floated warp yarns, good drapability, very pliable weave and used for forming curved surfaces [73]. Figures 2.9 (b) shows examples of Sateen 3/2 or 3-harness and Sateen 4/3 or 4-harness or crowfoot that can be found as a reinforcing structure in textile composites [69].




Figure 2.9: Examples of designs of Composite Reinforcing Materials (a) Twill 2/2 (b) Sateen.

The fundamental weave is the basis of more complex patterns in preform construction used for upgrading the design effect or the mechanical properties of the preform. Figure 2.10 shows some examples of weave design based on the fundamental weave.




Figure 2.10: Examples of modified and complex design weave (continued).




Figure 2.10: Examples of modified and complex design weave (continuation).

Therefore, in order to indicate that the weave design is based on the preform properties, weave tightness can be used as an indicator. The weave tightness or connectivity is determined by weave design and it quantifies the freedom of yarns to move. To characterize the weave tightness, the equation (2.1) is used [69];

$$Tightness = \frac{2}{f_{wa} + f_{we}} \quad (2.1)$$

where; f_{wa} = the number of warp intersections

f_{we} = the number of weft intersections

Lower tightness value indicates fewer fixations of the yarns in a preform, less stability and better drapability. As the preform is less stable, it tends to be distorted easily, while higher tightness means higher crimp and this deteriorates preform strength.

Yarn crimp is the waviness of warp yarn and weft yarn interlacing together to produce preform construction as shown in Figure 2.11. It is defined as a percentage of the excess length of the yarn axis over preform length [74]. Thus, it has great influence on the preform performance and the geometry of the preform. Therefore, crimp is effected by yarn count, preform structure and weaving tensions. If the weft yarn (or the preform in the weft direction) is kept at a low tension whilst the tension in the warp direction is high, then there will be considerable crimp in the weft and very little in the warp [74-75]. In summary, the build-up of crimp is caused by:

REFERENCES

1. Cheung, H., Ho, M., Lau, K., Cardona, F. and Hui, D. Natural fibre-reinforced composites for bioengineering composites and environmental engineering applications. *Composites: Part B*. 2009. 40: 655-663.
2. Madsen, B. and Gamstedt, E.K. Wood versus Plant Fibers: Similarities and Differences in Composite Applications. *Advances in Materials Science and Engineering*. 2013.
3. Brouwer, W.D.R. Natural Fibre Composites in Structural Components: Alternative Applications for Sisal? in *Common Fund for Commodities - Alternative Applications for Sisal and Henequen*. Rome. 2000.
4. Shibata, S., Cao, Y. and Fukumoto, I. Flexural modulus of the unidirectional and random composites made from biodegradable resin and bamboo and kenaf fibres. *Composites: Part A*. 2008. 39: 640-646.
5. Bledzki, Zhang, A.K., and Chate, A. Natural-fibre-reinforced polyurethane microfoams. *Composites Science and Technology*. 2001. 61(16): 2405-2411.
6. Cristaldi, G., Latteri, A., Recca, G. and Cicala G. Composites Based on Natural Fibre Fabrics. In: Dubrovski, P.D. (Ed). *Woven Fabric Engineering*. Sciyo: Intech. pp. 317-342; 2010.
7. Ji, Hwang, M. S. and Ji, D.S. The Effects of Yarn Number and Liquid Ammonia Treatment on the Physical Properties of Hemp Woven Fabrics. *Fibers and Polymers*. 2012. 13(10): 1335-1340.
8. Seok, Y. S., Lee., J. T., Ji, D. S., Kim, M. W., Lee, S. H. and Youn, J. R. Viscoelastic and thermal behavior of woven hemp fiber reinforced poly(lactic acid) composites. *Composites: Part B*. 2012. 43: 856-860.
9. Stocchi, A., Lauke, B., Va'zquez, A. and Bernal, C. A novel fiber treatment applied to woven jute fabric/vinylester laminates. *Composites: Part A*. 2006. 38: 1337-1343.

10. Aitharaju, V. R. and Averill, R. C. Three-dimensional properties of woven-fabric composites. *Composites Science and Technology*. 1999. 59: 190-1911.
11. Jawaid, M. and Khalil, H. P. S. A. Cellulosic/synthetic fibre reinforced polymer hybrid composites: A review. *Carbohydrate Polymers*. 2011. 86(1): 1-18.
12. Sakthvei, M. and Ramesh, S. Mechanical Properties of Natural Fibre (Banana, Coir, Sisal) Polymer Composites. *Science Park*. 2013. 1(1) 1-6.
13. Beckwith, S. W. Natural fiber reinforcement materials; lower cost technology for composite applications. *Composiite Fabrication*. 2003. 19(11) 12-16.
14. Girisha, S., Rangasrinivas, G. Tensile Properties of Natural Fiber Reinforced Epoxy-hybrid Composites. *International Journal of Modern Engineering Research*. 2012. 2(2): 471-474.
15. Rashdi, A. A. A., Sapuan, S. M., Ahmad, M. M. H. M. and Khalina, A. Combined Effects of Water Absorption Due to Water Immersion, Soil Buried and Natural Weather on Mechanical Properties of Kenaf Fibre Unsaturated Polyester Composites (kfupc). *International Journal of Mechanical and Materials Engineering*. 2010. 5(1): 11-17.
16. Ochi, S., Mechanical properties of kenaf fibers and kenaf/PLA composites. *Mechanics of Materials*. 2008. 40: 446-452.
17. Asumani, O., Reid, R. and Paskaramoorthy, R. The effects of alkali-silane treatment on the tensile and flexural properties of short fibre non-woven kenaf reinforced polypropylene composites. *Composites Part A: Applied Science and Manufacturing*. 2012. 43(9): 1431-1440.
18. Bernard, M., Khalina, A., Aidy, A., Janius, R., Faizal, M., Sasnah, H. K. and Sanuddin A. B. The effect of processing parameters on the mechanical properties of kenaf fibre plastic composite. *Materials and Design Journal*. 2011. 32: 1039-1043.
19. Mallick, P. K. Random Fiber Composites. In: Mallick, P. K. (Ed). *Composites Engineering Handbook.*, New York: Taylor & Francis. pp. 891-939; 1997.

20. Ahmad, J.Y. Introduction to polymer composites. In: Ahmad, J. Y. (Ed). *Machining of polymer*. New York: Springer Science. pp. 1-35; 2009.
21. Ramaswamy G. N., Sellers T., Tao W. and Crook L. G. Kenaf nonwovens as substrates for laminations. *Indian Crop Prod.* 2003;17:1-8.
22. Rot, K., Huskic, M., Makarovic, M., Mlakar, T. L. and Zigon, M. Interfacial effects in glass fibre composites as a function of unsaturated polyester resin composition. *Composite: Part A.* 2001. 32: 511-516.
23. Taj, S., Munawar, M.A. and Khan, S. U. Natural fiber-reinforced polymer composites. *Pakistan Acad. Sci.* 2007. 44(2): 129-144.
24. Bijwe, J. *Optimization of Woven Carbon Fiber Reinforced Composites for Structural and Tribological Applications.* 2007. Unpublished.
25. Shindo, Y., Narita, F. and Sato, T. Analysis of mode II interlaminar fracture and damage behavior in end notched flexure testing of GFRP woven laminates at cryogenic temperatures. *Acta Mechanica.* 2006. 187: 231-240.
26. Causa, A. and Netravali, A. Characterization and Measurement of Textile Fabric Properties. In: Schwartz, P. (Ed). *Structure and Mechanics of Textile Fiber Assemblies.* Cambridge: Woodhead Publishing Limited. pp. 4-47; 2008.
27. John, L. S., Blair, P. D., Eyring, G., Bull, E. T. and Adams, J. *Advanced Materials by Design.* Washington: Government Printing Office. 1988.
28. Gutiérrez, E. and Bono, F. *Review of industrial manufacturing capacity for fibre-reinforced polymers as prospective structural components in Shipping Containers.* Luxembourg: Publications Office of the European Union. 2013.
29. Tungjitpornkull, S. and Sombatsompop, N. Processing technique and fiber orientation angle affecting the mechanical properties of E-glass fiber reinforced wood/PVC composites. *Journal of Materials Processing Technology.* 2009. 209(6): 3079-3088.
30. Abraham, D., Matthews, S. and McIlhagger, R. A comparison of physical properties of glass fibre epoxy composites produced by wet lay-up with autoclave consolidation and resin transfer moulding. *Composites Part A: Applied Science and Manufacturing.* 1998. 29(7): 795-801.

31. Strong, A.B. *Fundamentals of Composites Manufacturing: Materials, Methods and Applications*. 2nd Ed. USA: Society of Manufacturing Engineers. 2008.
32. Alavudeen, A., Thiruchitrambalam, M., Venkateshwaran N., and Athijayamani, A. Review of Natural Fiber Reinforced Woven Composite. *Rev. Adv. Mater. Sci.* 2011. 27: 146-150.
33. Zampaloni, M., Pourboghrat, F., Yankovich, S. A., Rodgers, B. N., Moore, J., Drzal, L. T., Mohanty, A. K., and Misra, M. Kenaf natural fiber reinforced polypropylene composites: A discussion on manufacturing problems and solutions. *Composites Part A: Applied Science and Manufacturing*. 2007. 38(6): 1569-1580.
34. Ku, H., Wang, H., Pattarachaiyakoop, N. and Trada, M. A review on the tensile properties of natural fiber reinforced polymer composites. *Composites Part B: Engineering*. 2011. 42(4): 856-873.
35. Dhakal, H., Zhang, Z. and Richardson, M. Effect of water absorption on the mechanical properties of hemp fibre reinforced unsaturated polyester composites. *Composites Science and Technology*. 2007. 67(7): 1674-1683.
36. Ayre, Stevens, B.G., Chapman, K., Webber K. D., Dagnon, C. L., D'Souza, K. L. and Nandika A. Viscoelastic properties of kenaf bast fiber in relation to stem age. *Textile Research Journal*, 2009. 79(11): 973-980.
37. Mallick, P.K. Thermoplastics and Thermoplastic-matrix Composites for Lightweight Automotive Structures. In: Mallick, P.K. (Ed). *Materials, Design and Manufacturing for Lightweight Vehicles*. Cambridge: Woodhead Publishing Limited. pp. 174-207; 2010.
38. Lee, C. K., Cho, M. S., Kim, I. H., Lee, Y. and Nam, J. D. Preparation and Physical Properties of the Biocomposite, Cellulose Diacetate/Kenaf Fiber Sized with Poly(Vinyl Alcohol). *Macromolecular Research*. 2010. 18(6): 566-570.
39. Harun, J. Kenaf – Its Establishment and Journey towards Energizing the Wood-based and Biocomposite Industry in Malaysia. *International Conference on Prospects of Jute & Kenaf as Natural Fibers*. Dhaka: Bangladesh-China Friendship Conference Centre. 2009.

40. Ministry of Plantation Industries and Commodities Malaysia. (2009). *Ucapan : Majlis Menandatangani MOU Antara LTN dan Anchor Company*. Retrived on December 13, 2011, from <http://www.kppk.gov.my>.
41. Kurodaa, K. I., Izumib, A. N., Mazumderc, B. B., Ohtanic, Y. and Sameshimac, K. Evaluation of chemical composition of the core and bast lignins of variety Chinpi-3 kenaf (*Hibiscus cannabinus* L.) by pyrolysis–gas chromatography/mass spectrometry and cupric oxide oxidation. *Industrial Crops and Products*. 2005. 22: 223-232.
42. Mosello, A. A., Harun, J., Shamsi, S. R. F., Resalati, H., Tahir M. P., Ibrahim, R. and Mohammed, A. Z. A Review of Literatures Related to Kenaf as a Alternative for Pulpwoods. *Agricultural Journal*. 2010. 5(3): 131-138.
43. Rowell, R. M. *Opportunities for Composite Materials from Jute and Kenaf: The Hague, Netherlands, 26-29 October 1993*. Netherlands: FAO. 1993.
44. Akil, H. M., Omar, M.F., Mazuki, A.A.M., Safiee, S., Ishak, Z. A. M. and Bakar, A. A. Kenaf fiber reinforced composites: A review. *Material and Design*. 2011. 32: 4107-4121.
45. Vuure, A.V. Natural Fibre Composite; Recent Developments. *Innovation for Sustainable Production - i -SUP2008*. Bruges, Belgium: Site of Old Saint-John's. 2008.
46. Sreekumar, P. A. Matrices for natural-fibre reinforced composites. In: Pickering K.L. (Ed). *Properties and performance of natural-fibre composites*. Brimingham: Woodhead Pub. 2008.
47. Alvarez, V.A. and Vazquez, A. Effect of water sorption on the flexural properties of a fully biodegradable composite. *Journal of Composite Materials*. 2004. 38(13): 1165-1182.
48. Xue, L., Tabil, L. G. and Panigrahi, S. Chemical Treatments of Natural Fiber for Use in Natural Fiber-Reinforced Composites: A Review. *J Polym Environ*. 2007. 15: 25-33.
49. Cao, Y., Sakamoto, S. and Goda, K. Effects of Heat and Alkali Treatments on Mechnaical Properties of Kenaf Fibers. *16th International Conference on Composite Materials*. Kyoto. 2007.

50. Aji, I. S., Sapuan, M.S., Zainudin E.S. and Abdan, K. Kenaf fibres as reinforcement for polymeric composites: A review. *International Journal of Mechanical and Materials Engineering (IJMME)*. 2009. 4(3): 239-248.
51. El-Shekeli, Sapuan, M. S., Khalina, A., Zainuddin, E. S. and Al-Shuja'a, O. M. Effect of Alkali Treatment on Mechanical and Thermal Properties of Kenaf Fiber-reinforced Thermoplastic Polyurethane Composite. *J Therm Anal Calorim*, 2012.
52. Huda, M. S., Drzal, L. T., Mohanty, A. K. and Misra, M. Effect of fiber surface-treatments on the properties of laminated biocomposites from poly(lactic acid) (PLA) and kenaf fiber. *Composites Science and Technology*, 2008. 68: 424-432.
53. Lee, B. H., Kim, H. J. and Yu, W. R. Fabrication of Long and Discontinuous Natural Fiber Reinforced Polypropylene Biocomposites and Their Mechanical Properties. *Fibers and Polymers*. 2009. 10(1): 83-90.
54. El-Shekeil, Y.A., Sapuan, M.S., Abdan, K. and Zainudin, E.S. Influence of fiber content on the mechanical and thermal properties of Kenaf fiber reinforced thermoplastic polyurethane composites. *Materials and Design*. 2012. 40: 299-303.
55. Azrin, A. R., Seang, C. T., Ahmad, R. and Mariatti, J. M. Impact and Flexural Properties of Imbalance Plain Woven Coir and Kenaf Composite. *Applied Mechanics and Materials*. 2012. 271: 81-85.
56. Ifju, P.G., Ettinger, S., Jenkins, D. and Martinez, L. Composite materials for micro air vehicles. *A materials and processes odyssey*. 2001. 1926-1937.
57. Long, A.C. *Design and Manufacture of Textile Composite*. Cambridge: Woodhead Publishing Limited. 2005.
58. Peerzada, M. H., Abbasi, S. A. and Khatri, A. Effect of weave structure on tensile strength and yarn crimp of three-dimensional fibre woven fabric. *Sci.Int.(Lahore)*. 2012. 24(1): p. 47-50.
59. Ogin, S.L. Textile-reinforced composite materials. In: Horrocks, A. R. and Anand, S. (Ed). *Handbook of Technical Textiles*. Abington Cambridge: Woodhead publishing limited. pp. 264-279: 2004.

60. Karahan, M. Investigation of damage initiation and propagation in 2 X 2 twill woven carbon/epoxy multi-layer composites. *Textile Research Journal*. 2011. 81(4): 412-428.
61. Liu, Q. and Hughes, M. The fracture behaviour and toughness of woven flax fibre reinforced epoxy composites. *Composites: Part A*. 2008 39: 1644-1652.
62. Odegard, G., Searles, K. and Kumosa, M. A continuum elastic-plastic model for woven-fabric/polymer-matrix composite materials under biaxial stresses. *Composites Science and Technology*. 2001. 61(16): 2501-2510.
63. Broucke, B.V.D., Hamila, N., Middendorf, P., Lomov, S. V., Boisse, P. and Verpoest, I. Determination of the mechanical properties of textile-reinforced composites taking into account textile forming parameters. *Int. J. Mater Form*. 2010. 3: 1351-1361.
64. Ifju, P.G. Composite Materials. In: Sharpe, J. And William N. (Ed). *Springer Handbook of Experimental Solid Mechanics*. London: Springer Handbook. 2008.
65. Naik, R. A. Failure analysis of woven and braided fabric reinforced composites. *Journal of Composite Materials*. 1995. 29(17): 2334-2363.
66. Lee, S. K., Byun, J. H. and Hong, S. H. Effect of fiber geometry on the elastic constants of the plain woven fabric reinforced aluminum matrix composites. *Materials Science and Engineering: A*. 2003. 347(1): 346-358.
67. Ferdinand P. B., Johnston, E. R. DeWolf, J. and Mazurek, D. *Mechanics of materials*. 6th Ed. New York: McGraw-Hill. 2012.
68. Taylor, M.A.. *Technology of Textile Properties*. 3rd. Ed. Forbes Publication. 2007.
69. Lomov, S. and Verpoest, I. Manufacturing and Internal Geometry of Textiles in Design and Manufacturing of Textile Composite. In: Long, A. C. (Ed). *Design and Manufacture of Textile Composite*. Cambridge: Woodhead Publishing Limited. pp. 1-61; 2005.
70. Das, S. Recycling and Life Cycle Issues for Lightweight Vehicles. In: Mallick, P. K. (Ed). *Materials, Design and Manufacturing for Lightweight Vehicles*. Cambridge: Woodhead Publishing Limited. pp. 309-331; 2010.

71. Ngai, T. Carbon-carbon composite. In: Lee, S. M. (Ed). *Handbook of composite reinforcements*. Wiley-VCH. pp. 41-70; 1993.
72. Hexcel. *Technical Fabrics Handbook*. Texas: Hexcel Reinforcement for Composites.
73. Vandeurzen, Ph., Ivens, J. and Verpoest, I. Three-dimensional Micromechanical Analysis of Woven Fabric J.Composites: 1. Geometric Analysis. *Composites Science and Technology*. 1996. 56: 1303-1315.
74. Hu, J. *Structure and Mechanics of Woven Fabrics*. Cambridge: Woodhead Publishing Limited. 2004.
75. Lord, P. R. and Mohamed, M.H. *Weaving: Conversation of Yarn to Fabric*. Durham, England: Merrow Publishing. 1992.
76. Dauda, B., Oyadiji, S. O. and Potluri, P. Characterising Mechanical Properties of Braided and Woven Textile Composite Beams. *Applied Composite Material*. 2008. 16(1): 15-31.
77. Karahan, M. The effect of fibre volume fraction on damage initiation and propagation of woven carbon-epoxy multi-layer composites. *Textile Research Journal*. 2011. 82(1): 45-61.
78. Warmoeskerken, V. A. and Warmoeskerken, M. M. C. G. *Process Engineering and Industrial Enzyme*. In: Paulo, A.C. and Gubitz, G.M. (Ed). *Textile Processing with Enzymes*. Cambridge: Woodhead Publishing Limited. pp. 120-154; 2003.
79. Maria, A. Introduction to modeling and simulation. *Proceedings of the 29th conference on Winter Simulation*. Atlanta: IEEE Computer Society. 1997. pp. 7-13.
80. Tan, P., Tong, L. and Steven, G. P. Modelling for predicting the mechanical properties of textile composites - A review. *Composites Part A: Applied Science and Manufacturing*. 1997. 28(11): 903-922.
81. Hivet, G. Wending, A., Salle, E. V., Laine, B. and Boisse, P. Modeling strategies for fabrics unit cell geometry application to permeability simulations. *International Journal of Material Forming*. 2010. 3(1): 727-730.

82. Carvelli, V., Corazza, C. and Poggi, C. Mechanical modelling of monofilament technical textiles. *Computational Materials Science*. 2008. 42(4): 679-691.
83. Lomov, S.V., Huysmans, G., Luo, Y., Parnas, R. S., Prodromou, A., Verpoest, I. and Phelan, F. R. Textile composites: modelling strategies. *Composites Part A: Applied Science and Manufacturing*. 2001. 32(10): 1379-1394.
84. Manfredi, L. B., Rodríguez, E. S., Maria, W. P. and Analía, V. Thermal degradation and fire resistance of unsaturated polyester, modified acrylic resins and their composites with natural fibres. *Polymer Degradation and Stability*. 2006. 91(2): 255-261.
85. Farias, M. A., Farina, M. Z., Pezzin, M. P. T. and Silva D. A. K. Unsaturated polyester composites reinforced with fiber and powder of peach palm: Mechanical characterization and water absorption profile. *Materials Science and Engineering: C*. 2009. 29(2): 510-513.
86. Pereira, C.M.C., Herrero, M., Labajos, F. M., Marques, A. T. And Rives, V. Preparation and properties of new flame retardant unsaturated polyester nanocomposites based on layered double hydroxides. *Polymer Degradation and Stability*. 2009. 94(6): 939-946.
87. Dai, K. S., Jiang, L., Yu, S., Yang, B., Yuen, W., Richard K. K. and Yuan, H. Unsaturated polyester resins modified with phosphorus-containing groups: Effects on thermal properties and flammability. *Polymer Degradation and Stability*. 2013. 98(10): 2033-2040.
88. Böhme, F., Komber, H. and Jafari, S. H. Synthesis and characterization of a novel unsaturated polyester based on poly(trimethylene terephthalate). *Polymer*. 2006. 47(6): 1892-1898.
89. Waigaonkar, S., Babu, B. and Rajput, A. Curing studies of unsaturated polyester resin used in FRP products. *Indian Journal of Engineering & Materials Sciences*. 2011. 18(1): 31-39.
90. Alms, J. B., Glancey, J. L. and Advani, S. G. Mechanical properties of composite structures fabricated with the vacuum induced preform relaxation process. *Composite Structures*, 2010. 92(12): 2811-2816.

91. Correia, N. C., Long, A. C., Rudd, C. D., Šimáček, P. and Advani, S. G. Analysis of the vacuum infusion moulding process: I. Analytical formulation. *Composites Part A: Applied Science and Manufacturing*. 2005. 36(12): 1645-1656.
92. Brouwer, W.D., Herpt, E. C. F. C. V. and Labordus, M. Vacuum injection moulding for large structural applications. *Composites Part A: Applied Science and Manufacturing*. 2003. 34(6): 551-558.
93. Modi, D. M. J., Long, A. and Rudd, C. Analysis of pressure profile and flow progression in the vacuum infusion process. *Composites Science and Technology*. 2009. 69: 1458-1464.
94. Yenilmez, B., Senan, M. and Sozer, E. M. Variation of part thickness and compaction pressure in vacuum infusion process. *Composites Science and Technology*. 2009. 69(11–12): 1710-1719.
95. Ashoria, J., Harun, A., Raverty, W. D. and Yusoff, M. N. M. Chemical and morphological characteristics of Malaysian cultivated kenaf (*Hibiscus cannabinus*) fiber. *Polymer-Plastics Technology and Engineering*. 2006. 45(1): 131-134.
96. Rouison, D., Sain, M. and Couturier, M. Resin transfer molding of natural fiber reinforced composites: cure simulation. *Composites Science and Technology*. 2004. 64(5): 629-644.
97. American Society for Testing and Materials. *Standard Test Method for Twist in Single Spun Yarns by the Untwist-Retwist Method*. United States, D 1422. 2004.
98. Lomov, S. V., Gusakov, A.V., Huysmans, G., Prodromou, A. and Verpoest, I. Textile geometry preprocessor for meso-mechanical models of woven composites. *Composites Science and Technology*. 2000. 60: 2083-2095.
99. American Society for Testing and Materials. *Standard Test Method for Tensile Properties of Yarns by the Single-Strand Method*. United States, D 2256. 2004.
100. Sgriccia, N. and Hawley, M. Characterization of natural fiber surfaces. *Sixteenth International Conference on Composite Materials*. Kyoto Japan: Japan Society for Composite Materials. 2007.

101. Smith, W. and Hashemi, J. *Foundations of Material Science and Engineering*. 5th ed. Singapore: McGraw Hill. 2011.
102. Rashdi, A. A. A., Sapuan, M. S., Ahmad M. M. H. M. and Khalina, A. *Water absorption and tensile properties of soil buried kenaf fibre reinforced unsaturated polyester composites (KFRUPC)*. *Journal of Food, Agriculture & Environment*. 2009. **7**(3 & 4): 908-911.
103. American Society for Testing and Materials. *Standard Test Method for Breaking Force and Elongation of Textile Fabrics (Strip Method)*. United States, D 5035. 2004.
104. Yenilmez, B. and Sozer, E. M. Compaction of e-glass fabric preforms in the Vacuum Infusion Process, A: Characterization experiments. *Composites Part A: Applied Science and Manufacturing*. 2009. **40**(4): 499-510.
105. American Society for Testing and Materials. *Standard Test Method for Tensile Properties of Polymer Matrix Composite Materials*. United States, D3039. 2004.
106. American Society for Testing and Materials. *ASTM Standard for Fabric-Reinforced Textile Composite Materials*. United States, D 6856. 2008.
107. Davis, J.R. Tensile testing of fiber-reinforced composites. In: Davis, J.R. (Ed). *Tensile testing*. 2nd Ed. United State: ASM International. 2004.
108. American Society for Testing and Materials. *Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials*. United States, D 790. 2004.
109. Ku, H., Cheng, Y. M., Snook, C. And Baddeley, D. Drop weight impact test fracture of vinyl ester composites: micrographs of pilot study. *Journal of Composite Materials*. 2005. **39**(18): 1607-1620.
110. Askeland, D., Fulay, P. and Wright, W.J. *The science and engineering of materials*. Canada: Thomson Engineering. 2011.
111. American Society for Testing and Materials. *Standard Test Methods for High Speed Puncture Properties of Plastics Using Load and Displacement Sensors*. United States, D 3763. 2004.
112. Dubrovski, P. D. Woven Fabrics and Ultraviolet Protection. In: Dubrovski, P. D. (Ed). *Woven Fabric Engineering*. Sciyo: Intech. pp. 273-296; 2010.

113. Sun, B., Wang, Y., Wang, P., Hong H. and Gu, B. Investigations of puncture behaviors of woven fabrics from finite element analyses and experimental tests. *Textile Research Journal*. 2011. 81(10): 992-1007.
114. Jacobs, M. and Thomas, S. Biofibers and biocomposites. *Carbohydrate Polymers*. 2008. 71: 343-364.
115. Bonnafous, C., Touchard, F. and Arnault, L. C. Damage Mechanisms in Hemp-Fibre Woven Fabric Composite, and Comparison with Glass-Fibre Composite. *Polymers & Polymer Composites*. 2010. 19(7): 543-552.
116. Behera, B. K., Militky, J., Mishra, R. and Kremenakova, D. Modeling of Woven Fabrics Geometry and Properties. In: Jeon, H. Y. (Ed). *Woven Fabrics*. InTech. 2012.
117. Rukuižienė, Z. and Milasius, R. Influence of Reed on Fabric Inequality in Width. *Fibres & Textiles in Eastern Europe*. 2006. 14(4): 44-47.
118. Sondhelm, W.S. Technical fabric structures - 1. Woven fabrics. In: Horrocks, A. R. and Anand, S. C. (Ed). *Handbook of technical textiles*. Abington Cambridge: Woodhead publishing limited. 2004.
119. Abu Bakar, I. A., O.K., Bordas, S. and Rabczuk, T. Optimization of elastic properties and weaving patterns of woven composites. *Composite Structures*. 2013. 100: 575-591.
120. Vatankhah, E. Importance of the Cloth Fell Position and Its Specification Methods. In: Dubrovski, P.D. (Ed). *Woven Fabric Engineering*. Sciyo: InTech Europe. pp. 93-110; 2010.
121. Rukuižienė, Z. and E. K. Investigation of Initial Warp Tension and Weave Influence on Warp Yarn Diameter Projections. *Fibres & Textiles in Eastern Europe*. 2013. 21(5): 43-48.
122. Adomaitienė, A., G. R. and Kumpikaitė, E. Influence of Weaving Loom Setting Parameters on Changes of Woven Fabric Structure and Mechanical Properties. *Materials Science*. 2011. 17(4): 417-422.
123. Turhan, Y., S. T. and Eren, R. Statistical and computational intelligence tools for the analyses of warp tension in different back-rest oscillations. *Information Sciences*. 2007. 177: 5237-5252.
124. Stein, F. (1929). *The Nature of Plain Weave*. Retrived on Mei 9, 2014, from http://www.cs.arizona.edu/patterns/weaving/articles/sf_weave.pdf

125. Shamsudin, M. H. and York, C. B. Mechanically coupled laminates with balanced plain weave. *Composite Structures*. 2014. 107: 416-428.
126. Kos, I., Schwarz., I. G. and Sutton, K. Influence of Warp Density on Physical-Mechanical Properties of Coated Fabric. *Procedia Engineering*. 2014. 69: 881 - 889.
127. Jilei, Y. D., Yu, Z. J., Lacy, T. E., Xue, Y., Toghiani, H., Horstemeyer, M. F. and Pittman, C. U. Kenaf Bast Fiber Bundle–Reinforced Unsaturated Polyester Composites. IV: Effects of Fiber Loadings and Aspect Ratios on Composite Tensile Properties. *Forest Prod. J.* 2010. 60(7/8): 582-591.
128. Mishra, V. and Biswas, S. Physical and Mechanical Properties of Bi-directional Jute Fiber epoxy Composites. *Procedia Engineering*. 2013. 51: 561 - 566.
129. Asi, O. Effect of different woven linear densities on the bearing strength behaviour of glass fiber reinforced epoxy composites pinned joints. *Composite Structures*. 2009. 90: 43-52.
130. Azrin, A. R., Jaafar, M., Roslan, M. N. and Ariffin, S. Mechanical Properties Evaluation of Woven Coir and Kevlar Reinforced Epoxy Composites. *Advanced Materials Research*. 2011. 277: 36-42.
131. Sebe, G., Cetin, N. S., Hill, C. S. and Hughes, M. RTM Hemp Fibre-Reinforced Polyester Composites. *Applied Composite Materials*. 2000. 7: 341-349.
132. Dhakal, H. N., Zhang, Z. Y., Richardson, M. O. W. and Errajhi, O. A. Z. The low velocity impact response of non-woven hemp fibre reinforced unsaturated polyester composites. *Composite Structures*. 2007. 81(4): 559-567.
133. Huber, T., Bickerton, S., Müssig, J., Pang, S. and Staiger, M. P. Flexural and impact properties of all-cellulose composite laminates. *Composites Science and Technology*. 2013. 88: p. 92-98.
134. Cristian, I., Nauman, S., Boussu, F. and Koncar, V. A Study of Strength Transfer from tow to Textile Composite Using Different Reinforcement Architectures. *Application Composite Material*. 2012. 19: 427-442.
135. Ratim, M., Bonnia, N. N. and Surip, S. N. (2010). The effect of woven and non-woven fiber structure on mechanical properties polyester composite

- reinforced kenaf. *Procd. of the Second ASEAN Workshop on Advanced Material Science and Nanotechnology*. Penang, SIRIM. pp. 131-135.
136. Sreekala, M. Textile composites based on natural fibers. In: Pothan, L. A. and Thomas, S. (Ed). *Natural Fibre Reinforced Polymer Composites: From Macro to Nanoscale*. Paris, France: Archives contemporaines. pp. 202-227; 2009.
137. Swolfs, Y., Crauwels., L., Gorbatikh, L. and Verpoest, I. The influence of weave architecture on the mechanical properties of self-reinforced polypropylene. *Composites: Part A*. 2013 53: 129-136.
138. Ehrhardt, A. Groner, S. and Becthold. T. Swelling Behaviour of Cellulosic Fibres – Part I: Changes in Physical Properties. *Fbres & Textiles*. 2007. 15(5-6): 64-65.
139. Qin, C., Soykeabkaew, N., Xiuyuan, N. & Peijs, T. The effect of fibre volume fraction and mercerization on the properties of all-cellulose composites. *Carbohydrate Polymers*, 2008. 71: 458-467.
140. John, M. J. and Anandjiwala, R. D. Recent Developments in Chemical Modification and Characterization of Natural Fiber-Reinforced Composites. *Polymer Composites*. 2008. 29(2): 187-207.
141. Paul, S. A., Boudene, A., Ibos, L., Candau, Y. and Sabu, T. Effect of fiber loading and chemical treatments on thermophysical properties of banana fiber/polypropylene commingled composite materials. *Composites: Part A*. 2008. 39: 1582-1588.
142. Xue, P., Cao, J. and Chen, J. Integrated micro/macro-mechanical model of woven fabric composites under large deformation. *Composite Structures*. 2005. 70(1): 69-80.
143. Jacob, M., Thomas, S. and Varughese, K. Novel woven sisal fabric reinforced natural rubber composites: tensile and swelling characteristics. *Journal of Composite Materials*. 2006. 40(16): 1471-1485.
144. Pinto, M. A., Chalivendra, V. B., Kim, Y. K. and Lewis, A. F. Effect of surface treatment and Z-axis reinforcement on the interlaminar fracture of jute/epoxy laminated composites. *Engineering Fracture Mechanics*. 2013 114: 104-114.

145. Vallo, C., Vazquez, J. M., Cyras, A. and Viviana, P. Effect of chemical treatment on the mechanical properties of starch-based blends reinforced with sisal fibre. *Journal of Composite Materials*. 2004. 38(16): 1387-1399.
146. Mohanty, A. K., Misra, M. and Drzal, L. T. Surface modifications of natural fibers and performance of the resulting biocomposites: an overview. *Composite Interfaces*. 2001. 8(5): 313-343.
147. Rokbi, M., Osmani, H., Imad, A. and Benseddiq, N. Effect of chemical treatment on flexure properties of natural fiber reinforced composite. *Procedia Engineering*. 2011. 10: 2092-2097.
148. Gu, H. Tensile and bending behaviours of laminates with various fabric orientations. *Material and design*. 2006. 27: 1086-1089.
149. Zhangying, S., Xiongyan, Z., Xing, W. and Jinsong, M. Predicting the elastic properties of sisal fiber reinforced polypropylene composites by a new method based on generalized method of cells and laminate analogy approach. *Composites Science and Technology*. 2014. 91: 45-49.
150. Mattsson, D., Joffe, R. and Varna, J. Damage in NCF composites under tension: Effect of layer stacking sequence. *Engineering fracture mechanics*. 2008. 75: 2666-2682.
151. Gerlac, R., Palast, A., Petrinic, N., Horning, A., Wiegand, J., Siviour, C. R. and Hufenbach, W. The interface between matrix pockets and fibres bundles under impact loading. *Composite Science and Technology*. 2009. 69: 2024-2026.
152. Gerlac, R., Siviour, C. R., Wiegand, J. and Petrinic, N. In-plane and through thickness properties, failures, modes, damage and delamination in 3D woven carbon fibre composites subjected to impact loading.. *Composite Science and Technology*. 2012. 72: 397-411.
153. Mariatti, M., Nasir, M. and Ismail, H. Determination of the influence of stacking structure, float length and pressure time on the flexural properties of satin laminated composite using a factorial design. *Polymer Testing*. 2002. 21: 807-814.
154. Sakurabaa, H., Matsumoto, T. And Hayashikawa, T. A Study on the Flexural Behavior of CFRP Box Beams with Different Laminate Structures. *Procedia Engineering*. 2011. 14: 1845-1854.

155. Naik, N., Shirao, P. and Reddy, B. Ballistic impact behaviour of woven fabric composites: Parametric studies. *Materials Science and Engineering: A*. 2005. 412(1): 104-116.
156. Zabala, H., Aretxabaleta, L., Castillo, G., Urien, J. and Aurrekoetxea, J., Impact velocity effect on the delamination of woven carbon–epoxy plates subjected to low-velocity equienergetic impact loads. *Composites Science and Technology*. 2014. 94: 48-53.
157. Zahid, B. and Chen, X. Impact evaluation of Kevlar-based angle-interlock woven textile composite structures. *Journal of Reinforced Plastics and Composites*. 2013. 32(12): 925-932.
158. Zhang, D. Y.S., Chen, L., Zhang, S. And Ning Pan. Influence of fabric structure and thickness on the ballistic impact behavior of Ultrahigh molecular weight polyethylene composite laminate. *Materials and Design* 2014. 54: 315-322.
159. Nayak, N., B. A. and Dutaa A. L. Ballistic performance of laminated composites against military impactors: experimental and numerical studies. In: *Dymat 2009: 9th international conference on the mechanical and physical behaviour of materials under dynamic loading*. Brussels, Belgium: EDP Sciences. 2009.
160. Aktas, A., Aktas, M. and Turan, F. The effect of stacking sequence on the impact and post-impact behavior of woven/knit fabric glass/epoxy hybrid composites. *Composite Structures*, 2013. 103: 119-135.
161. Ishak, M., Leman, Z., Sapuan, S. M., Edeerozey, A. M. M. and Othman, I. S. Mechanical properties of kenaf bast and core fibre reinforced unsaturated polyester composites. In: *IOP Conference Series: Materials Science and Engineering*. IOP Publishing. 2010.
1162. Aziz, S. H. and Ansell, M. P. The effect of alkalization and fibre alignment on the mechanical and thermal properties of kenaf bast fibre: part1-polyester resin matrix. *Composites Science and Technology*. 2004. 64(9): 1219-1230.
163. Kafi, A. A., Magniez, K. And Bronwyn L. F. Effect of manufacturing process on the flexural, fracture toughness, and thermo-mechanical properties of bio-composites. *Composites: Part A*. 2011. 42: 993-999.