

FINITE ELEMENT SIMULATION OF MACHINING AISI 1045 STEEL USING
UNCOATED CARBIDE TOOL

NABILA AFIF BINTI MOHMD ARIFIN

A thesis submitted in partial
fulfillment of the requirement for the award of
Master Degree of Mechanical Engineering

Faculty of Mechanical and Manufacturing Engineering
Universiti Tun Hussein Onn Malaysia

JUNE 2012

ACKNOWLEDGEMENT

Alhamdulillah, all praise to Allah, the most merciful and great caring and also salutation on prophet great reverence Muhammad, his whole family and ruler's friends because with Allah's bless I have managed to completed this study successfully.

My gratitude and sincere thanks goes to my supervisor, Dr. Erween Abd. Rahim for his advice and patience throughout my study. I will never ever forget his help and cooperation in completing this study.

Last but not least, this page will not complete without my deepest appreciation for my parents, fiancée, siblings and friends for all the supports given to me. Hopefully, Allah S.W.T will give rewards to all people who involved directly and indirectly above their cooperation in this study, InsyaAllah.



PERPUSTAKAAN TUNJUKU TOLAKAMINAH

ABSTRACT

In recent years, finite element methods (FEM) have become widely used in research and industrial applications because of the advancements in computational efficiency and speed. FEM is a useful tool for the analysis of metal cutting process where this method provide better prediction of process variables whereas interaction of the tool and the chip can also be examined. Much cutting force models have been developed to predict the machining parameter. Most focus mainly on dry conditions even though coolants are widely used in practical machining. Research for modeling of minimal quantity lubricant (MQL) conditions is scarce and not really established. The use of coolants in machining makes it very difficult to determine the friction coefficient at the tool-chip interface. Hence, a better understanding of friction modeling is required in order to produce more realistic finite element models of machining process. In this study, a rigorous investigation on the role played by the implemented friction model within a 2D simulation was carried out. The simulation tool used for the purpose of this study is DEFORM2D. DEFORM 2D can simulate large deformation accompanied by elastic, plastic, thermal and friction effects. The simulation results on cutting forces and temperature were compared with experimental measurement in order to verify whether it is possible to identify the best friction model and indicate the consistency and accuracy of the results when conducting the comparison. From the result, it shows that friction models affect predicted result for both cutting force and temperature in dry and MQL conditions.

ABSTRAK

Beberapa tahun kebelakangan ini, kaedah unsur terhingga (FEM) telah digunakan secara meluas dalam bidang penyelidikan dan perindustrian disebabkan oleh kemajuan dan kecekapan dalam pengiraan. FEM adalah kaedah yang berguna untuk analisis proses pemotongan logam di mana kaedah ini menyediakan ramalan yang lebih baik bagi pembolehubah proses manakala interaksi antara mata alat dan tatal juga boleh diperiksa. Banyak model daya pemotongan telah dibangunkan untuk meramal parameter pemesinan. Tumpuan paling utama adalah pada keadaan kering walaupun bahan penyejuk digunakan secara meluas dalam proses pemesinan yang praktikal. Penyelidikan untuk pemodelan bagi keadaan kuantiti minima pelincir (MQL) adalah terhad dan tidak benar-benar dibuktikan. Penggunaan bahan penyejuk dalam proses pemesinan menyukarkan pekali geseran untuk ditentukan. Oleh itu, pemahaman yang baik bagi model geseran diperlukan untuk menghasilkan model unsur terhingga yang lebih realistik dalam proses pemesinan. Dalam kajian ini, penyiasatan yang rapi mengenai peranan yang dimainkan oleh model geseran telah dijalankan menggunakan simulasi 2D. Perisian FEM yang digunakan untuk tujuan kajian ini adalah DEFORM 2D. DEFORM 2D mampu menjalankan simulasi bagi ubah bentuk yang besar yang disertai oleh elastik, plastik, kesan haba dan geseran. Keputusan simulasi daya pemotongan dan suhu dibandingkan dengan pengukuran eksperimen untuk mengesahkan jika ia adalah mungkin untuk mengenalpasti model geseran terbaik dan menunjukkan ketepatan keputusan semasa perbandingan dilakukan. Keputusan menunjukkan bahawa model geseran mempengaruhi hasil yang diramal untuk daya pemotongan dan suhu dalam keadaan MQL dan kering.

CONTENTS

| | | |
|------------------|--------------------------------|------------|
| | TITLE | i |
| | DECLARATION | ii |
| | DEDICATION | iii |
| | ACKNOWLEDGEMENT | iv |
| | ABSTRACT | v |
| | ABSTRAK | vi |
| | TABLE OF CONTENTS | vii |
| | LIST OF TABLES | xi |
| | LIST OF FIGURES | xii |
| | LIST OF SYMBOLS | xiv |
| | | |
| CHAPTER 1 | INTRODUCTION | 1 |
| | 1.1 Introduction | 1 |
| | 1.2 Problem Statement | 3 |
| | 1.3 Objectives of Study | 4 |
| | 1.4 Scope of Study | 4 |
| | 1.5 Rationale | 4 |
| | 1.6 Overview | 5 |
| | | |
| CHAPTER 2 | LITERATURE REVIEW | 6 |
| | 2.1 Introduction | 6 |
| | 2.2 Mechanics of metal cutting | 7 |
| | 2.2.1 Orthogonal cutting | 7 |
| | 2.2.2 Cutting force in turning | 11 |

| | | |
|-------|----------------------------------|----|
| 2.2.3 | Cutting temperature in turning | 12 |
| 2.3 | Minimum quantity lubricant (MQL) | 14 |
| 2.4 | Finite element analysis | 16 |
| 2.4.1 | Finite element formulation | 18 |
| 2.4.2 | Modelling of material properties | 20 |
| 2.5 | Friction model | 21 |
| 2.5.1 | Friction models for machining | 22 |
| 2.6 | Conclusion | 24 |

CHAPTER 3 METHODOLOGY 25

| | | |
|-------|--|----|
| 3.1 | Introduction | 25 |
| 3.2 | Experimental setup | 26 |
| 3.2.1 | Cutting tool material | 26 |
| 3.2.2 | Workpiece material | 27 |
| 3.2.3 | Machining test and cutting conditions | 28 |
| 3.2.4 | Force measurement | 29 |
| 3.2.5 | Temperature measurement | 31 |
| 3.2.6 | Lubrication technique and cutting fluid lubricant | 34 |
| 3.3 | FEM simulation of orthogonal cutting | 36 |
| 3.4 | Geometry modeling | 36 |
| 3.5 | Tool-Chip contact and Boundary Conditions | 37 |
| 3.6 | Mesh Generation | 39 |
| 3.7 | Methodology Flowchart | 41 |

CHAPTER 4 RESULT AND DISCUSSION 42

| | | |
|---------|---|----|
| 4.1 | Introduction | 42 |
| 4.2 | Comparison of FEM results with experimental data | 43 |
| 4.2.1 | Effect of various friction model | 45 |
| 4.2.1.1 | Dry conditions | 45 |

| | |
|---|-----------|
| 4.2.1.2 MQL conditions | 49 |
| 4.3 Effect of various friction coefficient for MQL | 53 |
| 4.4 Effect of various heat transfer coefficient for MQL | 55 |
| CHAPTER 5 CONCLUSION AND RECOMMENDATION | 58 |
| 5.1 Conclusion | 58 |
| 5.2 Recommendation for future works | 59 |
| REFERENCES | 60 |
| APPENDIX | 65 |



LIST OF TABLES

| | | |
|-----|---|----|
| 2.1 | Characteristics of synthetic esters and fatty alcohol | 15 |
| 3.1 | Cutting tool geometry | 26 |
| 3.2 | Composition of AISI 1045 | 27 |
| 3.3 | Properties of AISI 1045 | 27 |
| 3.4 | Summary of cutting conditions | 28 |
| 3.5 | MQL supplying system | 34 |
| 3.6 | Geometry Specification | 37 |
| 3.7 | Friction Models | 38 |
| 4.1 | FEM simulation result for cutting force and temperature compared with experimental data for dry condition | 46 |
| 4.2 | FEM simulation result for cutting force and temperature compared with experimental data for MQL condition | 49 |
| 4.3 | FEM simulation result for cutting force, F_z at different friction coefficient for MQL condition | 53 |
| 4.4 | FEM simulation result for temperature at different heat transfer coefficient for MQL condition | 55 |

LIST OF FIGURES

| | | |
|------|---|----|
| 1.1 | Turning Process | 2 |
| 2.1 | Orthogonal Cutting Geometry | 8 |
| 2.2 | Oblique Cutting Geometry | 8 |
| 2.3 | Schematic illustration of two-dimensional orthogonal cutting | 9 |
| 2.4 | Thin shear plane model | 10 |
| 2.5 | Thick shear plane model | 10 |
| 2.6 | Cutting (F_c) and thrust (F_t) force components of resultant tool force (F_r) | 11 |
| 2.7 | Region of heat generation in turning | 13 |
| 2.8 | Lagrangian definition | 18 |
| 2.9 | Eulerian definition | 19 |
| 2.10 | Explanation of contact between two surfaces | 21 |
| 2.11 | Static and kinetic friction | 22 |
| 2.12 | Stresses distribution on rake face | 23 |
| 3.1 | Cutting tool | 26 |
| 3.2 | Workpiece Material | 27 |
| 3.3 | NC Harrison lathe machine | 28 |
| 3.4 | A schematic for tool and work piece geometry | 29 |
| 3.5 | Dynamometer (Kistler 9257B) | 30 |
| 3.6 | Charge Amplifier (Kistler 5019 A) | 30 |
| 3.7 | K-type (chromel) thermocouple | 31 |
| 3.8 | Embedded thermocouple | 32 |
| 3.9 | Distance of thermocouple wire from tool tip | 32 |

| | | |
|------|---|----|
| 3.10 | Conductive silver paste | 33 |
| 3.11 | Epoxy | 33 |
| 3.12 | Multimeter | 33 |
| 3.13 | Ecosaver KEP-R | 34 |
| 3.14 | MQL oil | 35 |
| 3.15 | Nozzle distance | 35 |
| 3.16 | Geometry Modelling | 36 |
| 3.17 | Displacement boundary conditions applied to the workpiece and tool | 39 |
| 3.18 | Mesh distribution around the tool tip | 40 |
| 3.19 | Methodology flow chart | 41 |
| 4.1 | Temperature are observed at point on the rake face | 43 |
| 4.2 | Average cutting forces measured for FEM simulation | 44 |
| 4.3 | FEM results at different friction model compared with experimental data for dry condition | 47 |
| 4.4 | FEM results of temperature at different friction models for dry condition | 48 |
| 4.5 | FEM results of at different friction model compared with experimental data for MQL condition | 50 |
| 4.6 | FEM results of temperature at different friction models for MQL condition | 52 |
| 4.7 | FEM results for cutting force, F_z at different friction coefficient for MQL condition | 54 |
| 4.8 | FEM results for temperature at different heat transfer coefficient for MQL condition | 55 |
| 4.9 | FEM results of temperature at different heat transfer coefficient for MQL condition | 56 |

LIST OF SYMBOLS

| | | |
|----------|---|-------------------------------|
| V_c | - | Cutting speed (m/min) |
| f_r | - | Feed (mm/rev) |
| d | - | Depth of cut (mm) |
| F_r | - | Resultant force (N) |
| F_t | - | Thrust force (N) |
| F_c | - | Cutting force (N) |
| F_f | - | Frictional force (N) |
| N | - | Normal force (N) |
| m | - | Mass(kg) |
| g | - | Gravity(m/s ²) |
| μ | - | Coefficient of friction |
| α | - | Rake angle (°) |
| β | - | Clearance angle (°) |
| t_o | - | Uncut chip thickness (mm) |
| t_c | - | Chip thickness (mm) |
| l_c | - | Contact length (mm) |
| ALE | - | Arbitrary Lagrangian Eularian |
| BUE | - | Built up edge |
| FEM | - | Finite element method |
| MQL | - | Minimal Quantity Lubricant |
| NDM | - | Near dry machining |

CHAPTER 1

INTRODUCTION

1.1 Introduction

Metal cutting is a process in which, by action of a cutting edge (or edges) of a tool, unnecessary material is removed. It is one of the most common manufacturing processes for producing parts and obtaining specified geometrical dimensions and surface finish. Many studies and experiments were performed since beginning of the 20th century. One of the widely used machining processes is turning process. Turning is a process of removing excess material from the work piece to produce an asymmetric surface, in which the work piece rotates in a spindle and the tool moves in a plane perpendicular to the surface velocity of the job at the tool-job operation. Turning operations are performed on a machined tool called lathe and the process is shown in Figure 1.1.






Figure 1.1: Turning Process

The performance of a turning operation is greatly influenced by the application of cutting fluid, and, in this regard, turning operations can be classified into dry turning, turning with minimum quantity lubrication (MQL), flood turning, and cryogenic turning. Of these, flood turning is the most traditional technique and by far the most widely used in industry. The two major functions of cutting fluids are (i) to increase tool life and (ii) to improve the surface finish of manufactured parts. However, with the advent of various new tool materials and their deposition techniques, the tool lives of modern tools have increased significantly. Dry turning is characterised by the absence of any cutting fluid, and unlike MQL and cryogenic turning does not require any additional delivery system [1]. Consequently, dry turning has gained renewed interest for its potential environmental and economic benefits. Nevertheless, in spite of all its economic and environmental benefits, the dimensional accuracy and surface finish of component parts produced by dry turning should not be sacrificed [2]. In minimal quantity lubrication (MQL), a very small lubricant flow (ml/h instead of l/min) is used. In this case, the lubricant is directly sprayed on the cutting area. It guarantees a good level of lubrication, but the cooling action is very small and the chip removal mechanism is obtained by the air flow used to spread the lubricant [3].

1.2 Problem Statement

In recent years, finite element methods (FEM) have become widely used in research and industrial applications because of the advancements in computational efficiency and speed. FEM is a useful tool for the analysis of metal cutting process where this method provide better prediction of process variables whereas interaction of the tool and the chip can also be examined.

The understanding of interactions during the cutting process is a fundamental task where this knowledge enables tool makers to evaluate the performance of the cutting tool design. Besides, it also enables the users of cutting tools to evaluate the effects of the working conditions on tool life and on the quality of the final part. Many experimental observations with trial and error are needed for the optimization of cutting conditions. Furthermore, repeating the experiment to achieved desired optimized cutting condition will be expensive and time consuming. Hence, FEM is an effective method as it would decrease experimentation and reduce cost.

In addition, much cutting force models have been developed to predict the machining parameter. Most focus mainly on dry conditions even though coolants are widely used in practical machining. Beside, research for modeling of MQL conditions is scarce and not really established. As for FEM simulation of machining, the main problem is to determine the boundary conditions at the tool-chip interface. The use of coolants in machining makes it very difficult to determine the friction coefficient at the tool-chip interface. Hence, a better understanding of friction modeling is required in order to produce more realistic finite element models of machining process. The contact behavior between the chip and the tool is critical due to its effect on the tool performance. Furthermore, the coolant method will not only affect the friction coefficient but also the heat transfer coefficient between the tool and workpiece combination.

This study includes the effect of dry and MQL conditions on cutting force and temperature. It is expected that at the end of this project, a good agreement is obtained between simulation and experiment data to indicate that the simulation is capable of predicting cutting force and temperature.

1.3 Objective of study

The objectives of the proposed project are;

- i. To study effect of various friction models, in order to predict the tool temperature and cutting force using FEM in two different conditions; dry and MQL.
- ii. To investigate the effect of various heat transfer coefficient for MQL conditions.
- iii. To validate the simulations results by comparing with experimental result for dry and MQL conditions.
- iv. To propose the best possible friction model involved in dry and MQL turning process.

1.4 Scope of Study

The scopes of this study are:

- i. Deform 2D version 9.0 software
- ii. Simulation is performed in two conditions; dry and MQL
- iii. Cemented carbide is used as cutting tool.
- iv. Workpiece material is AISI 1045
- v. Experiment are running in fixed condition; Cutting speed, $V_c= 160$ m/min, feed, $f_r=0.15$ mm/rev, depth of cut, $d= 0.30$ mm
- vi. Friction model used are Coulomb, Shear, and Coulomb-Shear.

1.5 Rationale

The rationales of the present research are:

- i. Finite element analysis give better prediction of turning variables such as cutting forces, workpiece and tool temperature which is essential to the optimization of cutting tool design and cutting conditions such that product quality, productivity, and tool life are maximized.

- ii. FEM proved to be an efficient tool to optimize several industrial metal machining processes. The use of FEM in modeling of machining allows for considering process details that analytical models cannot handle and for predicting variables.

1.6 Overview

This study concentrates on finite element method used to simulate machining process. Simulations are running using the commercial software DEFORM 2D developed by Scientific Forming Technologies Corporation (STFC). Effects of machining parameters on cutting forces and temperature distribution are studied.

In Chapter 2, earlier experimental studies, results, and analyses reported in the literature on the topic are presented. General well known theories in metal cutting being discussed to well understand the mechanics of metal cutting. Literature on finite element analysis of machining also reviewed and discussed. Constitutive material model, material properties for these models, friction model are some of the important issues in the FEM simulation of metal cutting. Work reported in the literature addressing these issues is presented.

The experimental test procedure and the modelling of metal cutting are mentioned in Chapter 3. All results, both from experiments and simulations are given in Chapter 4. Simulations results are compared with the experimental results of this work. This work is discussed and concluded in Chapter 5. Some recommendations for future work are given in that chapter as well.

CHAPTER 2

LITERATURE REVIEW

2.1 Introduction

This chapter presents a review of literature related to experimental and numerical procedures, finite element method (FEM) in turning operation. Since finite element simulation is nowadays assuming a large relevance, many studies on this topic have been published. The present chapter starts with mechanics of metal cutting. Early attempts from the previous researchers considering development of FEM method are also being discussed.



PTTA UTHM
PERPUSTAKAAN TUNKU TUNJUKAN

2.2 Mechanics of Metal Cutting

Metal cutting is the process of removing unwanted material from the workpiece to obtain a part with high quality surfaces and accurate dimensions with acceptable tolerances. This process has represented a very large segment in industry since last century. It is estimated that 15 percent of the value of all mechanical components manufactured worldwide is derived from machining operations [4]. The metal cutting process includes different forms of machining process such as grinding, turning, milling, sawing, etc. For all these types of machining, the productions of chips have different forms and each process has unique chip morphology. Therefore, it is important to understand the mechanism of chip formation in order to understand the machining process.

In the middle of the 19th century, the old (trial and error) experimental method was the earliest way to develop models of the metal cutting process. The simplified models were also presented and used based on the shear zone theory [5]. The chip formation was assumed to take place as the result of shear actions in the shear zone. Later, finite element analysis was utilized, trying to optimize metal cutting processes. This opened a new way to investigate the state of stresses, strains, temperatures, and feed and cutting forces in the deformation zones. These models provide a better understanding of metal cutting and provided ways to do detailed studies of the effect of different parameters where the magnitude of some parameters such as the temperature cannot be easily measured experimentally.

2.2.1 Orthogonal Cutting

Metal cutting process can be divided into two basic categories; orthogonal and oblique metal cutting. In orthogonal metal cutting, the cutting edge is perpendicular to the relative cutting velocity and also normal to the feed direction, as shown in Figure 2.1. However in oblique cutting, the cutting edge is inclined at an acute angle to the direction of the cutting velocity as shown in Figure 2.2. During the machining, the tool will be given a certain position to obtain the amount of feed that will be removed from the workpiece. In general, the cutting edge of the tool will engage into the workpiece; therefore, high pressure and high temperature will occur at the front of the tool.




Figure 2.1: Orthogonal cutting geometry [6]




Figure 2.2: Oblique cutting geometry [6]

The easiest way to present the fundamentals of the orthogonal metal cutting process is by the two dimensional metal cutting geometry as shown in Figure 2.3. As the workpiece starts moving, the cutting edge penetrates into the workpiece and forces the chip to grow up so that the chip will be formed and moved along the rake face of the tool. This process causes high pressure and plastic deformation is expected to take place in the front of the cutting edge. The shape of the formed chip will be affected by the cutting conditions (cutting speed, feed and depth of cut), tool geometry and material properties.




Figure 2.3: Schematic illustration of two-dimensional orthogonal cutting [7]

The uncut chip thickness (t_0) is known as the feed while the deformed chip has a different chip thickness (t_c). The tool will be defined by rake angle (α) and relief or clearance angle (β). The rake angle is defined to be positive on the right side (clockwise from vertical) and negative on the left side (counter clockwise). The contact length (l_c) is defined as the distance from the tip of the tool to the point where the chip loses contact with the tool on the rake face. The friction between the chip and the tool plays a significant role in the cutting process because of the heat energy that is transferred into the workpiece. It may be reduced by optimized tool geometry, tool material, cutting speed, rake angle, and cutting fluid. Because of the high pressure and temperature, a built up edge (BUE) may exist near the tool tip.

In orthogonal machining the shearing action takes place along the shear plane so the chip will start to flow over the rake face. The shearing zone has been modelled using either one of two assumptions. Merchant developed an orthogonal cutting model by assuming the shear zone to be thin as shown in Figure 2.4.




Figure 2.4: Thin shear plane model [6]

Once the material approaches the shear plane, the plastic deformations begins. A thin shear zone is usually created at high cutting speeds. Some researchers had different assumptions where the shear zone would be thick as shown in Figure 2.5. This kind of shear zone is more complicated and normally seen when using low cutting speeds.




Figure 2.5: Thick shear plane model [6]

Both models have been used to analyze metal cutting processes where the thin shear zone relates to the shear plane angle, cutting condition, material properties, and friction behaviour, while the thick shear zone model is based on the slip-line theory [5].

2.2.2 Cutting Force in Turning

Knowing the forces that are acting in metal cutting is important for many reasons such as for the power requirement. Some parameters including the cutting speed, feed, and depth of cut influence the forces. Most likely, the forces can be reduced to two main forces in 2-D instead of three forces in 3-D.

In orthogonal cutting the resultant force (F_r) applied to the chip by the tool lies in a plane normal to the tool cutting edge (Figure 2.6). This force is usually determined, in experimental work, from the measurement of two orthogonal components: one in the direction of cutting (known as cutting force F_c), the other normal to the direction of cutting (known as thrust force F_t). The cutting or tangential force (F_c), acts downward on the tool tip allowing deflection of the workpiece upward. It supplies energy required for the cutting operation. The thrust force (F_t) acts in the longitudinal direction. It is also called the feed force because it is in the feed direction of the tool. This force tends to push the tool away from the chuck.




Figure 2.6: Cutting (F_c) and thrust (F_t) force components of resultant tool force (F_r)[6]

Many researchers have correlated the measured cutting force components acting on a tool with tool wear [8] relates the wear of the cutting tool to the temperatures and measured forces acting on the tool. Force is also considered by [9] in the determination of the temperature of a machine surface. He successfully shows that the forces acting on the flank face, even with sharp tool, have been shown to be the most significant contributor to the temperatures in the workpiece.

Force modeling in metal cutting is important for thermal analysis, tool life estimation, chatter prediction, and tool condition monitoring purposes. Significant efforts have been devoted to understanding the force profiles in metal cutting. Along with a laborious experimental approach, several numerical and analytical approaches have been proposed to model the chip formation process and the associated cutting forces. Finite element method (FEM) has been applied to simulate the machining process since the early 1970s. Since then, FEM with different derivatives has received widespread attention in numerical modelling of machining processes [10].

Although some successes have been gained in modelling the chip formation forces in metal cutting by FEM, it is not yet ready to be applied due to the fact that it is laborious and not very easily extended to practical 3-D turning cases.

2.2.3 Cutting Temperature in Turning

The total work done by the cutting tool in removing metal can be determined from the values of the forces components on the cutting tool. Approximately all of this work or energy is converted into heat, which is dissipated into the tool and workpiece material; the higher the forces on the tool, the more work is needed in material removal, which in turn affects temperature. At high temperature, the cutting tool if not enough hot hard may lose their stability quickly or wear out rapidly resulting in increased cutting forces, dimensional inaccuracy of the product and shorter tool life.

The magnitude of this cutting temperature increases, though in different degree, with the increase in cutting velocity, feed and depth of cut, as a result, high production machining is constrained by rise in temperature. This problem increases further with the increase in strength and hardness of the work material. Knowledge of the cutting temperature rise in cutting is important because increases in temperature will adversely affect the strength, hardness and wear resistance of the cutting tool, cause dimensional changes in the part being machined, making control

of dimensional accuracy difficult and can induce thermal damage to the machined surface, adversely affecting its properties and service life.

Three regions of heat generation can be distinguished in turning; the shear zone, the chip-tool interface and the tool-workpiece interface (Figure 2.7). The primary shear zones temperatures affect the mechanical properties of the workpiece-chip material and temperatures at the tool-chip interfaces influence tool wear.




Figure 2.7: Region of heat generation in turning [11]

Much research has been undertaken into measuring the temperatures generated during cutting operations. The main techniques used to evaluate the temperature during machining (tool-chip thermocouple, embedded thermocouple, and thermal radiation method) have been reviewed by [12] and are discussed below. Thermocouples have always been a popular transducer used in temperature measurement. Thermocouples are very rugged and inexpensive can operate over a wide temperature range. A thermocouple is created whenever two dissimilar metals touch and the contact produces a small open-circuit voltage as a function of temperature. If these two dissimilar materials are the cutting tool and the workpiece material, then this thermocouple is called a tool-chip or tool-work thermocouple.

The tool-work thermocouple technique is used to measure the cutting temperatures at the interface between the tool and the chip. This technique is easy to apply but only measures the mean temperature over the entire contact area [13]. High local of flash temperatures which may occur for a short period of time cannot be

REFERENCES

- 1 Islam, M.N., Boswell, B., Member IAENG. An Investigation of Surface Finish in Dry Turning. *Proceedings of the World Congress on Engineering*. July 6-8, 2011. London, U.K.
- 2 Rafai, N. H., Islam, M.N., Member IAENG. Comparison of Dry and Flood Turning in Terms of Quality of Turned Parts. *Proceedings of the World Congress on Engineering*. June 30-July 2, 2010. London, U.K.
- 3 Attanasio, A., Gelfi, M., Remino, C. (2006). Minimal quantity lubrication in turning: Effect on tool wear. *Wear*, 260(3), 333-338.
- 4 Astakhov, V.P. (2005). On the inadequacy of the single shear plane model of chip formation. *International Journal of Mechanical Sciences* ,47(11),1649-1672.
- 5 Shaw, M. C. (1996). *Metal Cutting Principles*. Oxford. Oxford University Press.
- 6 Maftah, A. (1998). *Finite Element Simulation Of Orthogonal Metal Cutting Using An Ale Approach*. University of Seventh April: Master's Thesis.
- 7 Kalpakjian, S. K.(1995). *Manufacturing engineering and technology*.3rd ed.: Addison-Wesley Publishing.
- 8 Young, H.T. (1996). Cutting temperature responses to flank wear,*Wear* 201,117-120.
- 9 Chu, T., Wallbank, J. (1998). Determination of the temperature of a machined surface. *J.Manuf.Sci.Eng.* 2(120), 259-263.
- 10 E.G. Ng, Aspinwall, D.K., Brazil, D., Monaghan J. (1999). Modeling of temperature and forces when orthogonally machining hardened steel, *Int. J. Mach. Tools Manuf.* 39, 885–903.

- 11 D. O'Sullivan, M. Cotterell (2001). Temperature measurement in single point turning. *Journal of Materials Processing Technology*, 118(3), 301-308.
- 12 Barrow, G. (1973). *Ann. CIRP*, 22, 203-211.
- 13 Byrne, G. (1987). Thermoelectric signal characteristics and average interfacial temperature in the machining of metals under geometrically defined conditions. *Int.J.Mach.Tools Manuf.* , 2 (27), 215-224.
- 14 Cozzens, D.A.Sutherland, J.W.,Olson,W.W. (1995). An investigation into the cutting fluid effects on temperature in the aluminium boring,SME MR 95-210. *Proceedings of the First International Machining and Grinding Conference*, 1995, 881-891.
- 15 Sharif, S.,Yusof, N.M., Idris, M.H.Ahmad, Z.A (2009). *Feasibility study of using vegetable oil as a cutting lubricant through the use of minimum quantity lubricant during machining*. Universiti Teknologi Malaysia, Department of Manufacturing and Industrial Engineering.
- 16 Suda, S. Y. (2002). A Synthetic Ester as an Optimal Cutting Fluid for Minimal Quantity Lubrication Machining. *Annals of the CIRP* , 51 (1), 95-98.
- 17 Weinert , K, Inasaki, I , Sutherland, J. W.,Wakabayashi, T. (2007). Dry Machining and Minimum Quantity Lubrication. *Annals of the CIRP*,53(2), 511-537.
- 18 Lopez, L.N. Lamikiz, A.,Sanchez, J.A., Cabanes,I (2001). Cutting conditions and tool optimization in the high speed milling of aluminium alloys. *Proc.ImechE Part B*, 215, 1257-1269.
- 19 Itoigawa, F., Childs.,T.H.,Nakamura,T.,Belluco,W. (2006). Effects and mechanisms in minimal quantity lubrication machining of an aluminium alloy. *Wear* , 260 (3), 339-344.
- 20 Rahman, M., Kumar, A.S, Salam, M.U. (2001). Evaluation of minimal quantities of lubricant in end milling. *Int J Adv Manuf Technol* 18(4), 235-241.
- 21 Rahman , M, Kumar AS, Salam MU. (2002). Experimental evaluation on the effect of minimal quantities of lubricant in milling. *Int J Adv Mach Tools Manuf* , 42(5), 539-547.
- 22 Wakabayashi, T, Inasaki I, Suda S, Yokota, H. (2003). Tribological characteristics and cutting performance of lubricant esters for semi-dry machining. *CIRP Ann*, 52 (1), 61-64.

- 23 Dhar, N.R., Kamuzzaman, M., Ahmed, M., (2006). Effect of minimum quantity lubrication (MQL) on tool wear and surface roughness in turning AISI 4340 steel. *J.Mater.Process.Technol.*,172, 299-304.
- 24 Machado, A.R., Wallbank, J.,(1997). The effect of extremely low lubricant volumes in machining. *Wear*, 210 (1-2), 76-82.
- 25 Usui, E. and Shirakashi, T. (1982). Mechanics of machining from descriptive to predictive theory, on the art of cutting metals. *ASME PED* ,7 , 13-35.
- 26 Iwata, K. (1984). Process modelling of orthogonal cutting by the rigid-plastic finite element method. *Journal of Materials and Technology*,106, 132-138.
- 27 Ceretti, E. W. (1996). Application of 2D FEM to chip formation in orthogonal cutting. *Journal of Material Processing Technology* , 59, 169-180.
- 28 Halil, B.,Engin, K.S., Erman, T. (2004). A comparison of orthogonal cutting data from experiments with three different finite element models. *International Journal of Machine Tools & Manufacture* , 44, 933-944.
- 29 Ceretti, E., Filice, L. (2007). ALE Simulation of Orthogonal Cutting: a New Approach to Model Heat Transfer phenomena at the Tool-Chip Interface. *Annals of the CIRP* , 56(1).
- 30 Klamecki, B.E. (1973). *Incipient chip formation in metal cutting- a three dimension finite element analysis*. Ph.D Thesis, University of Illinois, Urbana-Champaign.
- 31 Carroll, J. S. (1988). Finite Element Models of Orthogonal Cutting with Application to Single Point diamond Turning. *International Journal of Mechanical Sciences* , 30 (12), 889-920.
- 32 Shih, A.J and Yang, H.T.Y. (1993).Experimental and Finite Element Predictions of Residual Stresses due to Orthogonal Metal Cutting. *International Journal for Numerical Methods in Engineering*,36, 1487-1507.
- 33 Marusich T. D. and Ortiz M. (1995). Modelling and Simulation of High-Speed Machining. *International Journal for Numerical Methods in Engineering*, 38, 3675-3694.
- 34 Ozel,T. (2006).The influence of friction models on finite element simulations of machining. *International Journal of Machine Tools & Manufacture*, 46, 518-530.

- 35 Strenkowski, J. S. and Moon, K. J (1990). Finite element prediction of chip geometry and tool/workpiece temperature distributions in orthogonal metal cutting. *ASME Journal of Engineering for Industry*, 112, 313-318.
- 36 Childs, T. H. C. and Maekawa, K. (1990). Computer-aided simulation and experimental studies of chip flow and tool wear in the turning of low alloy steels by cemented carbide tools. *Wear*, 139, 235-250.
- 37 Belytschko, T., Kennedy, J. M. (1978). Computer models for subassembly simulation. *Nuclear Engineering and Design*, 49, 17-38.
- 38 Olovsson, L., Nilsson, L. and Simonsson, K. (1999). An ALE formulation for the solution of two-dimensional metal cutting problems. *Computers and Structures*, 72(4), 497-507.
- 39 Movahhedy, M, Gadala, M.S. and Altintas, Y. (2000). Simulation of the orthogonal metal cutting process using an Arbitrary Lagrangian Eulerian finite element method. *Journal of Material Processing Technology*, 103, 267-275.
- 40 Childs, T. (1998). Material Property Needs in Modeling Metal Machining. *Machining Science and Technology*, 2(2), 303-316.
- 41 Mathew, P. and Arya, N.S. (1993). Material properties from machining. *Dynamic Loading in Manufacturing and Service*, 33-39.
- 42 Shatla, M., Kerk, C. and Altan, T. (2001). Process Modeling in Machining. Part I: Determination of Flow Stress Data. *International Journal of Machine Tools and Manufacture*, 41(10), 1511-1534.
- 43 Shatla, M., Kerk, C. and Altan, T. (2001). Process Modeling in Machining. Part II: Validation and Applications of the Determined Flow Stress Data. *International Journal of Machine Tools and Manufacture*, 41(11), 1659-1680.
- 44 Filice, L., Micari, F., Rizutti, S., Umbrello, D. (2007). A critical analysis on the friction modelling in orthogonal machining. *International Journal of Machine Tools & Manufacture*, 47, 709-714.
- 45 http://www.efunda.com/materials/alloys/carbon_steels ,accessed on 24th February.
- 46 Yen, Y.C., Sohner, J., Lilly, B, Altan, T. (2004) Estimation of tool wear in orthogonal cutting using finite element analysis. *Journal of Material Processing technology*, 146, 82-91.
- 47 Al-Zkeri, I. A. (2007). *Finite element modeling of hard turning*. Ohio State University: Ph.D. Thesis.

- 48 Kops, L, Arenson, M. (1999). Convective heat transfer coefficients in turning. In: *Proceedings of the 15th Brazilian Congress of Mechanical Engineering*, Sao Paulo, Brazil.
- 49 Sreejith, P.S., (2008). Machining of 6061 aluminium alloy with MQL, dry and flooded lubricant conditions. *Materials Letters*, 62,276-278.
- 50 Boothroyd,G.,Knight, W.A (2006). *Fundamental of Machining and machine Tools*. Ohio.
- 51 Gouqin Shi, Xiaomin Deng, Chandrakanth Shet (2002). A finite element study of the friction in metal cutting. *Finite elemet in analysis and design*, 38, 863-883.
- 52 Shih, A.J , Chandrasekar, S.,Yang, H.T. (1990). Finite element simulation of metal cutting process with strain-rate and temperatures effects *Fundamental Issues in Machining, ASME*, 43, 11-24.
- 53 Iqbal, S.A. , Mativenga, P.T., Sheikh, M.A. (2008). A sensitivity study of the effects of interface heat transfer coefficient on FE modelling of machining process for a wide range of cutting speeds. *6th International Conference on Manufacturing Research*.
- 54 Yen, Y.C., Sohner, J., Lilly, B., Altan, T. (2004).Estimation of tool wear in orthogonal cutting using the finite element analysis. *Journal of materials processing technology*,146, 82-91.

